

TECHNICAL DATASHEET

Page:1 of 2

Product name: **TEKNOCOAT AQUA PRIMER 221-104 1001 WHITE OPAQUE**
Colour code: **1001 WHITE OPAQUE**

Description & Intended use:

This product is recommend for the industrial lacquering of wood-based substrates. Waterborne pigmented primer to be applied in roller machines. This product improves the bond between the board and the following direct printed PDL- build up. The Product is especially designed as a primer for production lines with line speed > 40m/min. Vacuum- and spray- application of Teknocoat Aqua Primer 221-104 is possible.

Characteristics:

Viscosity: 50 ± 10 sec. DIN 6mm/20°C*
Density at 20°C: 1,5 ± 0,2 kg/l
Solid Content: 60 - 70 by weight %, fast test halogen dryer (160°C, 1g; Internal test standard No. 26)
Pigments: Contains no lead-, cadmium- or chromate pigments
VOC: max. 1%
Classification: No migration of hazardous materials such as heavy metals.

Roller application:

Preparation: Stir well before use
Hardener: None
Thinner: If required, adjust viscosity with water
Viscosity: As delivered
Temperature: The best application-temperature is 20 – 35°C.
Film Weight: 2 x 15 - 30g/m² (wet) with intermediate drying per roller application.
Application: Roller coater, with a shore hardness of preferable 40 – 50 shore (Isobutylen/Isopren-Copolymer or EPDM-Prepolymer).
Drying: 10 – 15s at 130°C jet air dryer, with airspeed of 25 – 30 m/s and a fresh air proportion of 15%. Sufficient drying should be checked be by preliminary tests.

*Determined on day of product release.

Application technology advice, technical data or recommendations are carried out to the best of our ability, albeit non-binding exluding warranty and limitation on liability. This data sheet will be rendered invalid as soon as replaced by a revised version. Please request the latest version.

TECHNICAL DATASHEET

Page:2 of 2

Product name: TEKNOCOAT AQUA PRIMER 221-104 1001 WHITE OPAQUE

Colour code: 1001 WHITE OPAQUE

Vacuum/ spray-application: Vacuum- and spray-application is possible after adjusting the viscosity to processing conditions. We recommended to adjust the viscosity with water, please add in maximum 40%. For application and processing proposals please ask our representative.

Substrate: This product was especially developed for the direct printing and lacquering process of wood-based substrates. Please consult our technical staff prior to other application.

Storage: The product should be stored between 5°C and 30°C. At a temperature of 23 ± 2°C the product has a shelf life of up to 12 month, from produce date, in its original sealed trading unit. Higher temperatures reduce the shelf life. Protect from sunlight and frost.

Cleaning: Clean equipment with water directly after use.

Precautions: Refer to Health and Safety Data Sheet.

Health &Safety: Refer to Health and Safety Data Sheet.