
TYPE	UV-curing sealer
USE	Intermediate sealing of wood where high demands to abrasion is specified. Especially suitable for parquet.
SPECIAL PROPERTIES	UVILUX Sealer is especially developed as sealer and has excellent sanding properties.

TECHNICAL DATA

Variant	11	12
Delivery viscosity DIN 6 at 20 °C	180-200 s DIN 6	180-200 s DIN 6
Specific density kg/l	Approx. 1.06 kg/l	Approx. 1.14 kg/l
Solids, weight %	100	100
Total mass of solids g/l	Approx. 1050	Approx. 1140

Volatile organic compound (VOC) See Safety Data Sheet.

Storage Should not be exposed to temperatures above +40 °C.
To be protected against frost.
To be protected against direct sunlight.
Storage: See label.
Store in a tightly closed container.

Application method Roller coating.

Drying method The lacquer cures under UV-lamps.

DIRECTIONS FOR USE

Application data The lacquer is ready for use.

Drying Approx. 6 m/min. per lamp (80 W/cm).

Recommended amount to be applied 15-30 g/m² depending on required abrasion.

Cleaning If necessary, the roller may be cleaned with TEKNOSOLV 1129.

HEALTH AND SAFETY See Safety Data Sheet.

ADDITIONAL INFORMATION The lacquer contains reactive acrylate.
The lacquer is irritating to skin and eyes. Thus the use of gloves and eye protection is recommended.
Take off immediately all contaminated clothing.
Application by spray is not recommended as spray mist increases the health hazards.