

TYPE Water borne topcoat**USE** For wood panels and fiberboards
Suitable for line application
Suitable for curtain coating
Only for indoor use**SPECIAL PROPERTIES** Fast drying
Good stacking
Good levelling**TECHNICAL DATA****Density** Approx. 1.19-1.20 kg/l**Solids** Approx. 44-46 % by weight
Approx. 33-35 % by volume**Volatile organic compound (VOC)** See Safety Data Sheet.**Storage** See label**Gloss** Approx. 20-35 Gardner 60°**Colour** Available in different colours**System** TEKNOCOAT AQUA 2574-1X is used on water borne primers. It should be over coated with 100% UV.**DIRECTIONS FOR USE****Application method** Curtain coating**Drying time**

	20°C	20 min / 50°C
Handable	1 h	After cooling
Stacking	3 h	After cooling

Thinner Water**Cleaning** Water or TEKNOCLEAN 1954-00, 1T021010**HEALTH AND SAFETY** See Safety Data Sheet.