

---

<b>TYPE</b>	Water-borne topcoat
<b>USE</b>	For solid wood, MDF and fiber boards. Very suitable for line application. Only for indoor use
<b>SPECIAL PROPERTIES</b>	Very fast drying Very good stacking Good levelling Good filling properties

---

**TECHNICAL DATA**

<b>Density</b>	Approx. 1.03-1.25 kg/l, depending on the amount of pigments  Base 1: approx. 1.22 kg/l Base 2: approx. 1.12 kg/l Base 3: approx. 1.04 kg/l
<b>Solids</b>	Approx. 33-48 % by weight Approx. 30-36 % by volume, depending on the amount of pigments  Bas 1: approx. 48 % by weight, approx. 36 % by volume Bas 2: approx. 39 % by weight, approx. 32 % by volume Bas 3: approx. 33 % by weight, approx. 30 % by volume
<b>Volatile organic compound (VOC)</b>	See Safety Data Sheet
<b>Recommended amount to be applied</b>	90-130 g/m <sup>2</sup>
<b>Storage</b>	See label
<b>Gloss</b>	Approx. 5-60 Gardner 60°
<b>Colour</b>	Available in different colours and tintable with TEKNOCOLOR in gloss 35
<b>System</b>	TEKNOCOAT AQUA 2575-1X is used on water borne primers

**DIRECTIONS FOR USE**

<b>Application method</b>	Conventional spraying Airless spraying Airmix spraying									
<b>Drying time</b>	<table><thead><tr><th></th><th>20 °C</th><th>20 min / 50 °C</th></tr></thead><tbody><tr><td>Handable</td><td>1 h</td><td>After cooling</td></tr><tr><td>Stacking</td><td>2 h</td><td>After cooling</td></tr></tbody></table>		20 °C	20 min / 50 °C	Handable	1 h	After cooling	Stacking	2 h	After cooling
	20 °C	20 min / 50 °C								
Handable	1 h	After cooling								
Stacking	2 h	After cooling								
<b>Thinner</b>	Water									
<b>Cleaning</b>	Water or TEKNOCLEAN 1954-00, 1T021010.									

**HEALTH AND SAFETY** See Safety Data Sheet