

DATA SHEET 1469

2 04.12.2020

AQUATOP 2760-12

Top coat

PAINT TYPE AQUATOP 2760-12 is a water-borne, fast drying and weather resistant top coat that is based on

acrylic.

USAGE Wood-aluminium window frame parts that are protected from weathering.

Before using the product, the manufacturer should be contacted to check the suitability of the product

for the object in question.

TECHNICAL DATA

Solids 35 ±2% by volume

Volatile organic compound (VOC) abt. 44 g/l Specific gravity 1.18 ±0.02

Theoretical spreading rate 5.5 m²/l with dryfilm 60 μm

Drying time, +23°C, relative humidity 50% (glass plate 120 μm)

- dust free after about 30 min- touch dry after about 40 min

The drying times given are indicative because the product is intended for use on wooden substrates.

Overcoatable after 1 - 2 h

Thinner, clean up Water

Finish Semi-matt

Colours White

PTO

DIRECTION FOR USE Surface preparation

The surface must be clean and dry.

The moisture content of the wood is to be below 20%.

It is recommended that the wood is treated with an efficient wood preservative that protects it against rot, blue stain

fungi and mildew.

Application conditions

The temperature of the air, the surface and the paint shall be above +15°C and the relative humidity of the air below 80% during the time of application and drying. The best result is achieved when the temperature of the air is +23 -

+38°C, the relative humidity of the air 50 - 70% and the ventilation is good.

Application Before use stir the paint thoroughly.

The paint is especially suited for high-speed rotation bell. Apply about 150 µm wet film per coat. Also suitable for

spraying and electrostatic spraying.

STORAGE Must not freeze. The best storage temperature is between +10 - +25°C.

The information of this data sheet is normative and based on laboratory tests and practical experience. Teknos guarantees that the product quality conforms to our quality system. Teknos accepts, however, no liability for the actual application work, as this is to a great extent dependent on the conditions during handling and application. Teknos accepts no liability for any damage resulting from misapplication of the product. This product is intended for professional use only. This implies that the user possesses sufficient knowledge for using the product correctly with regard to technical and working safety aspects. The latest versions of Teknos data sheets, material safety data sheets and system sheets are on our home pages www.teknos.com.

