

**TEKNOTAR 200****Urethane Tar**

PAINT TYPE	TEKNOTAR 200 is a quick-drying two-pack urethane tar.
USAGE	To be used as a priming and top coat in paint system K45. TEKNOTAR 200 is suited for interior and exterior use and on submerged or subterranean steel structures. The paint can also be used on concrete surfaces.
SPECIAL PROPERTIES	TEKNOTAR 200 can be applied even in high humidity environments. TEKNOTAR 200 dries at temperatures as low as -10°C. TEKNOTAR 200 forms a thick, chemical resistant coating. The coating will provide surfaces with long-term protection against moisture and water.

TECHNICAL DATA

Mixing ratio	Base (Comp. A): Hardener (Comp B): TEKNOTAR 200 HARDENER	2 parts by volume 1 part by volume
Pot life, +23 °C	4 h	
Solids	60 ±2% by volume	
Total mass of solids	abt. 900 g/l	
Volatile organic compound (VOC)	abt. 400 g/l	
Recommended film thickness and theoretical spreading rate	Dry film (µm)	Wet film (µm) Theoretical spreading rate (m ² /l)
	100	167 6,0
	125	208 4,8

As many of the paint's properties will change if too thick coats are applied, it is not recommended that the product is applied to a film thickness that is more than double of the thickest recommended film.

Practical spreading rate The values depend on the application technique, surface conditions, overspray, etc.

Drying time, +23°C / 50% RH (dry film 100 µm)

- dust free (ISO 9117-3:2010) after 1 h
- touch dry (ISO 9117-5:2012) after 2 h

Overcoatable, 50% RH (dry film 100 µm)

surface temperature	by itself	
	min.	max.*
+5°C	after 36 h	after 10 days
+23°C	after 4 h	after 7 days

* Maximum overcoating interval without roughening.

Thinner, clean up TEKNOSOLV 9521

Finish Matt

Colours Black and brown

SAFETY MARKINGS See Safety Data Sheet.

DIRECTION FOR USE**Surface preparation**

Remove from the surfaces any contaminants that might be detrimental to surface preparation and painting. Remove also water-soluble salts by using appropriate methods. The surfaces are prepared according to the different materials as follows:

STEEL SURFACES: Remove mill scale and rust by blast cleaning to preparation grade Sa 2½ (standard ISO 8501-1). Roughening the surface of thin-plate improves the adhesion of the paint to the substrate.

ZINC SURFACES: Hot-dip-galvanized steel structures that are exposed to atmospheric corrosion can be painted if the surfaces are sweep blast-cleaned (SaS) till matt all over. Suitable cleaning agents are, e.g. aluminium oxide and natural sand. It is not recommended according to standard ISO 12944-5 to paint hot-dip-galvanized objects that are subjected to immersion strain. Painting of hot-dip-galvanized objects that are subjected to immersion strain must be discussed separately with Teknos.

It is recommended that new zinc-coated thin-plate structures are treated with sweep blast-cleaning (SaS). Surfaces that have been weathered to matt can be treated also with RENSA STEEL washing agent for galvanized surfaces.

CONCRETE SURFACES: The concrete must be at least 4 weeks old, well-hardened and solid. The water content of the top layer must not exceed 4% by weight.

Smooth down any spatter and irregularities on the surfaces by grinding. Brush away loose cement, sand and dust. Wash oily and greasy surfaces with detergent or solvent. Remove dense laitance if present by etching with RENSA ETCHING etching liquid or by grinding or blast-cleaning.

OLD PAINTED SURFACES SUITABLE FOR OVERCOATING: Any impurities that might be detrimental to the application of paint (e.g. grease and salts) are removed. The surfaces must be dry and clean. Old, painted surfaces that have exceeded the maximum overcoating time are to be roughened as well. Damaged parts are prepared in accordance with the requirements of the substrate and the maintenance coating.

The place and time of the preparation are to be chosen so that the prepared surface will not get dirty or damp before the subsequent treatment.

Prefabrication primer

KORRO E Epoxy, KORRO SE Zinc Epoxy and KORRO SS Zinc Silicate Prefabrication Primers can be used, when required.

Mixing of the components

Take into consideration the pot life of the mixture when estimating the amount to be mixed at a time. Before painting the base and hardener are mixed in right proportion. Stir thoroughly down to the bottom of the vessel. Inadequate stirring or incorrect mixing ratio results in imperfect curing and impaired film properties.

Application conditions

The surface to be painted has to be dry. During the application and drying period the temperature of the ambient air and the surface shall be above -10°C and the relative air humidity below 95%. The temperature of the paint shall be above +15°C during mixing and application.

Application

Apply by brush or airless spray. Use airless spray nozzle 0.018 - 0.026".

ADDITIONAL INFORMATION

The storage stability is shown on the label. Store indoors in a cool and dry place and in a tightly closed can. The hardener reacts with air humidity and therefore the opened can is to be kept carefully closed, and it is recommended to be used within 7 d of opening.

Additional instructive information for surface preparation can be found in standards EN ISO 12944-4 and ISO 8501-2.

The information of this data sheet is normative and based on laboratory tests and practical experience. Teknos guarantees that the product quality conforms to our quality system. Teknos accepts, however, no liability for the actual application work, as this is to a great extent dependent on the conditions during handling and application. Teknos accepts no liability for any damage resulting from misapplication of the product. This product is intended for professional use only. This implies that the user possesses sufficient knowledge for using the product correctly with regard to technical and working safety aspects. The latest versions of Teknos data sheets, material safety data sheets and system sheets are on our home pages www.teknos.com.



EN_232_Tuoteseloste.pdf