

TEKNOTOP 2981-01, a water borne intermediate product / topcoat for repair of industrial treated wood designated for outdoor use such as balconies and garden furniture.

Translucent colours in TEKNOTOP 2981-01 contain UV absorbers to maximise the coatings durability.

TECHNICAL DATA

Binder:	Synthetic binder	
Solid content:	Translucent:	Approx. 35 % w/w
	White:	Approx. 45 % w/w
Viscosity:	Approx. 13 s in DIN cup 4 mm at 20 °C	
Volatile organic compound (VOC):	See Safety Data Sheet.	
Theoretical consumption:	Approx. 10 m ² /l	
	May vary according to wood quality and application method.	
Colour range:	Depending on the base TEKNOTOP 2981-01 can be delivered in translucent and white colours.	
Gloss:	Semi-matt	

APPLICATION DETAILS

Pre-treatment:	The wood must be clean and free from wood dust and contamination. The moisture content of the wood should be approx. 13 % and should not exceed 15 %.	
	All softwood and non-durable hardwood for exterior use should either be vacuum impregnated (only softwood) or treated with a wood preservative.	
Application:	Flow coat	
	Due to evaporation, the solid content of the liquid must be adjusted with water regularly.	
Application conditions:	The product is delivered ready for use. Stir the product well before use.	
	Film thickness:	Approx. 100 µm wet
	Optimum temperature for products and surroundings:	18-22 °C
	Optimum relative air humidity:	Approx. 50 %
System treatment:	Intermediate treated parts must always be protected with a topcoat treatment before they are exposed to the influence of the weather	
Drying times:	Determined at 20 °C and 50 % relative humidity:	
	Dry to handle:	1-2 hours
	Dry to sand:	2-3 hours
	Thoroughly dry:	24 hours
	The drying time can be reduced using special drying systems to force drying. The drying times are approximate and may vary according to wood quality, temperatures, humidity, ventilation and film thickness.	
Cleaning:	The equipment is cleaned with water.	

HEALTH AND SAFETY See Safety Data Sheet.

ADDITIONAL INFORMATION

Pack size: 20 and 120 l

Storage: The product must be stored at temperatures above 5 °C. Shelf life in unopened containers: See “Best before date” on the label. Keep containers tightly closed after use.

The above information is normative and based on laboratory tests and practical experiences. The information is noncommittal, and we cannot accept liability for the results obtained under working conditions beyond our control, and consequently the buyer or the user is not released from the obligation to test the suitability of our products for specific means and application methods under the actual application conditions. Our liability covers only damage caused directly by defects in the products supplied by Teknos. The latest versions of Teknos' Technical Data Sheets and Safety Data Sheets are available from our homepage www.teknos.com.