

AQUAPRIMER 3140

primer

PAINT TYPE	Water-borne, alkyd and acrylic based universal primer for wooden surfaces.
USAGE	For wooden windows, outer doors, garden furniture and other wooden objects. Before using the product, the manufacturer should be contacted to check the suitability of the product for the object in question.
SPECIAL PROPERTIES	AQUAPRIMER 3140 has a good hiding power and it penetrates well into the wood forming a good adhesion to the surface to be painted. AQUAPRIMER 3140 dries quickly and it has excellent sanding and stacking properties. The product is developed for demanding objects where a low water absorption is required. Product is suitable for spray application.

TECHNICAL DATA	
Solids	33 ±2% by volume
Total mass of solids	abt. 580 g/l
Haihtuvat orgaaniset aineet (VOC)	See Safety Data Sheet
Theoretical spreading rate	8 m ² /l (wet film 150 g/m ² , dry film 40 µm)
Drying time, +20°C / RH 50 %	
- dust free	after 30 min
- touch dry	after 60 min
- fit for sanding and overcoatable on wood	after 30 - 60 min (wet film 120 µm)
	The drying times given are indicative because the product is intended for use on wooden substrates. When using accelerated drying ask for the instructions from the manufacturer.
Thinner, clean up	Water
Finish	Semi-matt
Colours	White
SAFETY MARKINGS	See Safety Data Sheet.

PTO

DIRECTION FOR USE**Surface preparation**

The surface must be clean and dry.

The moisture content of the wood is to be below 20%.

It is recommended that the wood is treated with an efficient wood preservative that protects it against rot, blue stain fungi and mildew.

Application conditions

The temperature of the air, the surface and the paint shall be above +15°C and the relative humidity of the air below 80% during the time of application and drying.

The best result is achieved when the temperature of the air is +23 - +38°C, the relative humidity of the air 50 - 70% and the ventilation is good.

Application

Before use stir the paint thoroughly.

Apply the paint by spray.

STORAGE

Must not freeze. The best storage temperature is between +10 - +25°C.

Storage life: 6 months.

The information of this data sheet is normative and based on laboratory tests and practical experience. Teknos guarantees that the product quality conforms to our quality system. Teknos accepts, however, no liability for the actual application work, as this is to a great extent dependent on the conditions during handling and application. Teknos accepts no liability for any damage resulting from misapplication of the product. This product is intended for professional use only. This implies that the user possesses sufficient knowledge for using the product correctly with regard to technical and working safety aspects. The latest versions of Teknos data sheets, material safety data sheets and system sheets are on our home pages www.teknos.com.



EN_2141_Tuoteseloste.pdf