

# TEKNODUR COMBI 3560-92

## 01 Dark Grey B D028; 01 Black B S037

### High-solid Polyurethane Paint

<b>PAINT TYPE</b>	TEKNODUR COMBI 3560-92 is a two pack polyaspartic based high-solid polyurethane paint where the hardener used is an aliphatic isocyanate resin.
<b>USAGE</b>	Used in weather resistant polyurethane system. As an anticorrosive pigmented the paint is suitable to use as one-layer paint on metal surfaces.
<b>SPECIAL PROPERTIES</b>	The paint produces a film with good mechanical and weather resistance. Because the paint is fast curing it is suitable for use in two pack line painting where the demand for productivity is high.

**TECHNICAL DATA**

<b>Mixing ratio</b>	Base (Comp. A): Hardener (Comp B): TEKNODUR HARDENER 7227	3 parts by volume 1 part by volume	
<b>Pot life, +23 °C</b>	15 min		
<b>Solids</b>	70 ±2% by volume		
<b>Total mass of solids</b>	abt. 1160 g/l		
<b>Volatile organic compound (VOC)</b>	abt. 280 g/l		
<b>Recommended film thickness and theoretical spreading rate</b>	Dry film (µm)	Wet film (µm)	Theoretical spreading rate (m <sup>2</sup> /l)
	120	171	5,8

As many of the paint's properties will change if too thick coats are applied, it is not recommended that the product is applied to a film thickness that is more than double of the thickest recommended film.

**Practical spreading rate** The values depend on the application technique, surface conditions, overspray, etc.

**Drying time, +23°C / 50% RH (dry film 120 µm)**

- dust free (ISO 9117-3:2010)	after 30 min
- touch dry (ISO 9117-5:2012)	after 1½ h
- through-dry (ISO 9117-1:2009)	after 2 h

**Overcoatable, 50% RH (dry film 120 µm)**

surface temperature	by itself	
	min.	max.*
<b>+5°C</b>	after 8 h	after 24 h
<b>+23°C</b>	after 1 h	after 8 h

\* Maximum overcoating interval without roughening.

<b>Thinner</b>	Standard thinner: TEKNOSOLV 9526
<b>Clean up</b>	TEKNOCLEAN 6496
<b>Finish</b>	Semigloss
<b>Colours</b>	Atlas Copco 01 Dark Grey B D028, Atlas Copco 01 Black B S037
<b>SAFETY MARKINGS</b>	See Safety Data Sheet.

**DIRECTION FOR USE****Surface preparation**

Remove from the surfaces any contaminants that might be detrimental to surface preparation and painting. Remove also water-soluble salts by using appropriate methods. The surfaces are prepared according to the different materials as follows:

**STEEL SURFACES:** Remove mill scale and rust by blast-cleaning to preparation grade Sa 2½ (ISO 8501-1). The profile of the blast-cleaned surface should be coarse (reference comparator "G") ISO 8503-2 (G). The surface of thin-plate can be prepared e.g. by phosphating.

**OLD PAINTED SURFACES SUITABLE FOR OVERCOATING:** Any impurities that might be detrimental to the application of paint (e.g. grease and salts) are removed. The surfaces must be dry and clean. Old, painted surfaces that have exceeded the maximum overcoating time are to be roughened as well or cleaned using alcohol (isopropanol) or emulsifying wash. Damaged parts are prepared in accordance with the requirements of the substrate and the maintenance coating.

**ZINC SURFACES:** Hot-dip-galvanized steel structures that are exposed to atmospheric corrosion can be painted if the surfaces are sweep blast-cleaned (SaS) till matt all over. Suitable cleaning agents are, e.g. aluminium oxide and natural sand. It is not recommended according to standard ISO 12944-5 to paint hot-dip-galvanized objects that are subjected to immersion strain. Painting of hot-dip-galvanized objects that are subjected to immersion strain must be discussed separately with Teknos.

**ALUMINIUM SURFACES:** Treat the surfaces with an alkaline cleaning agent (RENSA STEEL). Surfaces that are exposed to weathering are also roughened up with sweep blast-cleaning (AlSaS) or sanding.

The place and time of the preparation are to be chosen so that the prepared surface will not get dirty or damp before the subsequent treatment.

**Mixing of the components**

Take into consideration the pot life of the mixture when estimating the amount to be mixed at a time. The base must be stirred until it is homogeneous before mixing the components. Before painting the base and hardener are mixed in right proportion. Stir thoroughly down to the bottom of the vessel. Inadequate stirring or incorrect mixing ratio results in imperfect curing and impaired film properties.

**Application**

Suitable primers are TEKNOPLAST PRIMER 5, TEKNODUR PRIMER 3411, TEKNOCRYL AQUA PRIMER 2788 or TEKNOCRYL AQUA COMBI 2780.

Before use stir the paint thoroughly.

When needed thin the paint 0 - 5 % with TEKNOSOLV 9526, TEKNOSOLV 9521 or with fast thinner TEKNOSOLV 1129.

Do not use universal diluents or thinners, since they may contain alcohol which will react with the hardener.

Apply by conventional spray or airless spray. Suitable airless spray nozzle size 0.011 - 0.015".

Before use clean the spray gun and paint vessels with the paint's own thinner.

It is recommended for the application to use 2-pack spraying equipment.

**Application conditions**

The surface to be painted must be dry and the relative air humidity below 80%. During the application and drying period the temperature of the ambient air and the surface shall be at least above -5°C, and the temperature of the paint above +15°C during mixing and spraying. The temperature of the surface and paint must be at least 3°C above the dew point of the ambient air.

The hardener of the paint and the ready paint mixture contain isocyanates. In poorly ventilated areas and especially when using spray application we recommend the use of a fresh air mask. In short or temporary work a mask with combined filter A2-P2 can be used. In this case eyes and face are to be protected.

**ADDITIONAL INFORMATION**

The hardener reacts with air humidity. Store indoors in a cool and dry place in a tightly closed can. The storage stability is limited.

Use opened hardener within two weeks.

Additional instructive information for surface preparation can be found in standards EN ISO 12944-4 and ISO 8501-2.

---

The information of this data sheet is normative and based on laboratory tests and practical experience. Teknos guarantees that the product quality conforms to our quality system. Teknos accepts, however, no liability for the actual application work, as this is to a great extent dependent on the conditions during handling and application. Teknos accepts no liability for any damage resulting from misapplication of the product. This product is intended for professional use only. This implies that the user possesses sufficient knowledge for using the product correctly with regard to technical and working safety aspects. The latest versions of Teknos data sheets, material safety data sheets and system sheets are on our home pages [www.teknos.com](http://www.teknos.com).

---



EN\_1732\_Tuoteseloste.pdf