

---

<b>PAINT TYPE</b>	Latex paint producing a flat finish.
<b>USAGE</b>	Painting indoors on wood, plaster and concrete in stables for animals, in warehouses and industrial premises.
<b>SPECIAL PROPERTIES</b>	<p>RANCH STALLFÄRG has high covering properties and good washability, it is easy to apply and does not spatter. Excellent also as primer under RANCH EXKLUSIV. Especially suited for use in premises where a risk of moulding exists.</p> <p>RANCH STALLFÄRG is not to be used in wetrooms, such as milk and washing rooms. For these rooms we recommend RANCH EXKLUSIV.</p>

---

**TECHNICAL DATA**

<b>Solids</b>	About 39 % by volume
<b>Volatile organic compound (VOC)</b>	EU VOC limit value (kat A/a): 30 g/l. The product's VOC: max. 30 g/l.
<b>Practical spreading rate</b>	About 5 m <sup>2</sup> /l
<b>Density</b>	abt. 1.5 g/ml
<b>Drying time +23°C, the relative air humidity 50%</b>	
- dust free	after 1 hour
<b>Overcoatable</b>	after 2 hours
<b>Thinner, clean up</b>	Water. Wash the equipment immediately after use with water.
<b>Finish</b>	Full-matt
<b>Colours</b>	White. Can be tinted to pastel colours in the Teknomix tinting system. The colour accuracy is not complete.

---

<b>SAFETY MARKINGS</b>	See Safety Data Sheet.
------------------------	------------------------

---

**DIRECTION FOR USE****Surface pretreatment and application**

Clean the surface from loose material. If the surface is moulded, clean with RENSA FACADE facade cleaner.

Unpainted wood and wood fibre plates must always be primed with FUTURA AQUA 3, otherwise there will be a risk of bleeding and miscolouring.

Unpainted surfaces are painted with two coats of RANCH STALLFÄRG. For the first coat the paint is diluted with about 10% of water. Top coat with undiluted paint. When painting simpler buildings, such as outbuildings, one thick coat with undiluted paint is usually enough.

Untreated plaster and concrete surfaces are primed with RANCH STALLFÄRG that has been diluted about 10% with water. Paint then one or two coats with undiluted RANCH STALLFÄRG. New concrete surfaces are not to be painted until they are 1-2 months old.

Previously painted surfaces are washed with RENSA FACADE facade cleaner. Rinse thoroughly with clean water. Loose and poorly adherent paint residues are scraped off. Scraped wooden surfaces are primed with FUTURA AQUA 3. Paint one or two coats with undiluted RANCH STALLFÄRG.

RANCH STALLFÄRG must not be painted directly on surfaces that have previously been painted with alkyd paint. Such surfaces are first to be primed with FUTURA AQUA 3.

Old lime surfaces and surfaces painted with glue paint are to be washed with high-pressure washer in order to remove all old paint. The surfaces are then primed with FUTURA AQUA 3 before top coating with RANCH STALLFÄRG. If RANCH STALLFÄRG is applied directly on old, poorly adherent paint, this may result in flaking.

Stir RANCH STALLFÄRG well before use and apply with brush, roller or spray.

**Application conditions**

The surface must be clean and dry.

During the application and drying period the temperature of the ambient air, the surface and the paint shall be above +5°C and the relative air humidity below 80%.

**STORAGE**

Must not freeze.

---

The information of this data sheet is based on laboratory tests and practical experience. The figures are for guidance only and depend on, for example, colour and gloss. As we have no control over the use and application conditions, we are only responsible for the quality of the product and guarantee that it conforms to our quality control. We accept no liability for any loss or damage resulting from the application of the product contrary to the directions or the intended use. The latest versions of our data sheets, material safety data sheets and system sheets are on our home pages [www.teknos.com](http://www.teknos.com).

---



RU\_1273\_Tuoteseloste.pdf