

TEKNOSEAL 4000, an aqueous product for sealing of end grain of new wood designated for exterior use such as windows and doors.

TECHNICAL DATA

Binder:	Synthetic binder.
Volatile organic compound (VOC):	See Safety Data Sheet.
Theoretical consumption:	May vary according to the quality and absorptive ability of the surface.
Colour range:	Colourless

APPLICATION DETAILS

Pre-treatment:	The wood must be clean and free from wood dust and contamination. The moisture content of the wood should be approx. 13 % and should not exceed 15 %.	
	All softwood and non-durable hardwood for exterior use should either be vacuum impregnated (only softwood) or treated with a wood preservative.	
Application:	Is applied by brush.	
Application conditions:	The product is delivered ready for use.	
	Optimum temperature for products and surroundings:	18-22 °C
	Optimum relative air humidity:	Approx. 50 %
System treatment:	Primed parts must always be protected with a topcoat treatment before they are exposed to the influence of the weather.	
Drying times:	Dry to handle: ½ -1 hour	
	The drying times are approximate and may vary according to wood quality, temperatures, humidity, ventilation and film thickness.	
Cleaning:	The equipment is cleaned with water.	

HEALTH AND SAFETY See Safety Data Sheet.

ADDITIONAL INFORMATION

Pack size:	0.75 l
Storage:	The product must be stored at temperatures above 5 °C. Shelf life in unopened containers: See "Best before date" on the label. Keep containers tightly closed after use.