
TEKNOSPRO BREPLASTA LF
light fine filler

PRODUCT TYPE	Ready-to-use, water-borne light all-purpose filler for dry spaces.
USAGE	Used for partial filling of joints and overall skimming of walls and ceilings in dry interior areas. The substrate can be gypsum, fibre board, concrete, lightweight concrete, plaster etc. Also suitable for filling of wall paper and painted surface joints.
SPECIAL PROPERTIES	TEKNOSPRO BREPLASTA LF has good adhesion and filling capabilities. The surface will be very smooth and therefore will be excellent for wall papering and painting.
APPROVALS	The product has been classified to Group M1 in Emission Classification of building materials. The product has CE approval. Additional information: see page 2: "CE MARKING".

TECHNICAL DATA

Solids	About 53 % by volume
Layer thickness	0 - 4 mm
Volatile organic compound (VOC)	The product is not included in the EU VOC directive.
Practical spreading rate	For skimming the entire surface, 1 l/m ² with 1 mm layer thickness. For partial filling of surfaces and filling of joints, two layers on gypsum board, abt. 0.3 l/m ² .
Particle size	Max. 0.15 mm
Density	1.1 g/ml
Drying time +23°C, the relative air humidity 50%	2 - 3 hours/mm depending on the layer thickness. The drying process will be slower in cold and/or damp.
Clean up	Water
Colours	Light grey
Packages (availability varies by country)	0,2 L, 0,4 L, 3 L, 10 L

SAFETY MARKINGS See Safety Data Sheet.

DIRECTION FOR USE**Surface preparation**

Clean new surfaces from dust and dirt.
Wash previously painted surfaces with RENSA SUPER paint cleaner.
Matt down hard or gloss surfaces by sanding and thereafter remove the dust.
Brittle surfaces and untreated wooden surfaces must be primed before the filler is applied.

Application method

Apply the filler with a trowel. The number of layers is dependent on the surface roughness.
The dried filler can be painted or wall-papered. Before wall-papering the filler surfaces must be primed with adhesive. The use of protective mask for eyes and face is recommended when sanding the filler.


Application conditions


The surface to be treated must be dry.
The temperature of the air, the surface and the filler shall be above +5°C and the relative humidity of the air below 80% during the time of application and drying.

Storage

To be stored in a cool place. Must not freeze. Storage stability is 1 year in unopened package.

CE MARKING

	
Teknos Oy Takkatie 3, P.O. Box 107 00371 Helsinki, Finland 13	
EN 15824 Finishing materials for plasterboard. Interior use. Hand application.	
Adhesion	> 0,35 MPa
Reaction to fire	B-s1, d0

	
Teknos Oy Takkatie 3, P.O. Box 107 00371 Helsinki, Finland 13	
EN 13963 Jointing materials for gypsum boards.	
Reaction to fire	B-s1, d0
Flexural strength	> 320 N



EN_1207_Tuoteseloste.pdf