
PRODUCT TYPE	Solvent-borne impregnating and drying oil for outdoor use.
USAGE	Used for surface treatment of new and faded hardwood, heat-treated wood and also for teak, oak and mahogany. The brown hardwood oil restores the original colour of discoloured hardwood. Typical objects are garden furniture, jetties, fences, trellises and doors. Protects the wood from drying, cracking and soiling. Optimum durability is achieved by renewing the WOODEX HARDWOOD OIL treatment yearly. Not suitable for greenhouses, hotbeds or shelters for livestock.

TECHNICAL DATA

Solids	About 35 % by volume
Volatile organic compound (VOC)	The product is not included in the EU VOC directive.
Practical spreading rate	Sawn timber 5 - 8 m ² /l Planed timber 8 - 10 m ² /l
Density	abt. 0.85 g/ml
Drying time, +23°C - touch dry - dry	after 8 hours after 16 hours The drying process will be slower in cold and/or damp.
Thinner, clean up	To be used without thinning. The equipment is washed immediately after use with TEKNOSOLV 1621 (solvent naphtha).
Finish	Is absorbed into the wood and does not usually form any visible film.
Colours	Brown and in spray can also clear
Weather resistance	For surfaces that are continuously exposed to weathering a renewed treatment is necessary once a year.
Packages (availability varies by country)	Brown: 0,5 L, 1 L and 500 ml spray Clear: 500 ml spray

SAFETY MARKINGS

See Safety Data Sheet.
NOTE! Because of the danger of self-ignition, any waste from the product, spray mist and soiled rags etc. are to be kept in a fire-proof place in air-tight containers. Immersion in water is also recommended.

PTO

DIRECTION FOR USE**Surface preparation**

Remove from the surface all loose matter, dirt and dust. Use RENSA TERRACE deck cleaner on surfaces to be treated, when needed. Rinse the surfaces thoroughly with water and allow to dry.

Remove old paint or varnish layers before the treatment.

Application

Before use stir the product thoroughly.

Stir well before application. Apply WOODEX HARDWOOD OIL by brush or sponge. Dipping can also be used.

Renew the treatment according to the quality of wood until the surface doesn't absorb more oil. Wipe off possible excess oil abt. 30 min after the application.

Application conditions

The surface to be treated must be dry. The relative moisture of the wood must be below 20% of the weight of the wood.

During the application and drying period the temperature of the ambient air, the surface and the product shall be above +10 °C and the relative air humidity below 80%.

The information of this data sheet is based on laboratory tests and practical experience. The figures are for guidance only and depend on, for example, colour and gloss. As we have no control over the use and application conditions, we are only responsible for the quality of the product and guarantee that it conforms to our quality control. We accept no liability for any loss or damage resulting from the application of the product contrary to the directions or the intended use. The latest versions of our data sheets, material safety data sheets and system sheets are on our home pages www.teknos.com.



EN_1700_Tuoteseloste.pdf