

TEKNOTOP 2980-00 is a water borne, industrial topcoat for wooden balcony parts. Leaves a flexible surface with extra UV-protection.

TEKNOTOP 2980-00 has been developed especially for application on horizontal surfaces, but can also be applied on vertical surfaces, and thus it can also be applied on garden furniture, playground equipment etc.

**TECHNICAL DATA**

Binder:	Synthetic binder.
Volatile organic compound (VOC):	See Safety Data Sheet.
Theoretical consumption:	Approx. 10 m <sup>2</sup> /l May vary according to wood quality and application method.
Colour range:	Base 1, 2, 3 and base T (white, opaque and translucent colours).
Gloss:	20

**APPLICATION DETAILS**

Pre-treatment:	The wood must be clean and free from wood dust and contamination. The moisture content of the wood should be approx. 13 % and should not exceed 15 %.		
	All softwood and non-durable hardwood for exterior use should either be vacuum impregnated (only softwood) or treated with a wood preservative.		
Application:	Airmix (aircoat) or airless by hand or in automatic spraying equipment.		
Application conditions:	The product is delivered ready for use. Stir the product well before use.		
	Film thickness:	Approx. 200 µm wet	
	Optimum temperature for products and surroundings:	18-22 °C	
	Optimum relative air humidity:	Approx. 50 %	
Spraying conditions:	<u>Nozzle</u>	<u>Pressure</u>	<u>Air support</u>
	Airless flat 0.28 mm	100-110 bar	
	Aircoat flat 0.28 mm	80-100 bar	1.0-1.5 bar
System treatment:	To be used in systems consisting of vacuum impregnation or wood preservatives as stated above and TEKNOPRIMER 2949.		
Drying times:	Determined at 20 °C and 50 % relative humidity:		
	Dry to handle:	2-3 hours	
	Dry to sand / recoat:	3-4 hours	
	The drying time can be reduced using special drying systems to force drying. The drying times are approximate and may vary according to wood quality, temperatures, humidity, ventilation and film thickness.		
Cleaning:	The equipment is cleaned with water.		

---

**HEALTH AND SAFETY**      See Safety Data Sheet.

**ADDITIONAL INFORMATION**

Pack size:                      20 and 120 l

Storage:                        The product must be stored at temperatures above 5 °C. Shelf life in unopened containers: See “Best before date” on the label. Keep containers tightly closed after use.

The above information is normative and based on laboratory tests and practical experiences. The information is noncommittal, and we cannot accept liability for the results obtained under working conditions beyond our control, and consequently the buyer or the user is not released from the obligation to test the suitability of our products for specific means and application methods under the actual application conditions. Our liability covers only damage caused directly by defects in the products supplied by Teknos. The latest versions of Teknos' Technical Data Sheets and Safety Data Sheets are available from our homepage [www.teknos.com](http://www.teknos.com).