

T E S T C E R T I F I C A T E

ST-15-12-02-23

Product: Coating system applied according to client's instruction (variant 15ae):
GORI 356 colourless
Aqua Primer 2900 translucent
Aqua Primer 3130 translucent
Aqua Top 2600 translucent

Client: Teknos A/S
Industrivej 19
6580 Vamdrup/ Denmark

Order: Carry out of selected tests of coating materials and coating systems for exterior wood according to VdL-Guideline 14/ EN 927-2

Test method: VdL-Guideline 14 / EN 927-3/ EN 927-5

Test report: 2713392

Test results:

Property	Result	Requirements according VdL-GL 14
Natural weathering EN 927-3 (bubble/ cracks/ flaking/ adhesion)	0/ 0/ 0/ 1	fulfilled
Water absorption EN 927-5	157 g/m ²	fulfilled
Blocking – adherence damages	a1/ a1/ a1 d0/ d0/ d0	fulfilled
Wet adhesion	2,2 MPa	fulfilled
Deformability	Cone A	fulfilled
Microfoam	2,8 air inclusions/cm	fulfilled

Dresden, 02 December 2015



Head of laboratory




Engineer in charge