

„MEŽA UN KOKSNES PRODUKTU PĒTNIECĪBAS UN ATTĪSTĪBAS INSTITŪTS” SIA
VAT No. LV 43603022749
Dobeles iela 41, Jelgava, LV-3001, Latvia
Phone +371 63010605 * E-mail meka@e-koks.lv * Web www.e-koks.lv



Additional extended application classification of reaction to fire in accordance with EN 13501-1:2018

This report is additional to that issued as dated 17.02.2021. Additional extended classification report supersedes original report and original classification report No. K10/2021 is no longer valid.

Issue number: K10/A/2021

Date of issue: 21.09.2021.

Sponsor: Teknos Norge AS.

Address: Industriveien 28, 3430 Spikkestad, Norway.

VAT No. NO961644739MVA.

Manufacturer and owner of classification report: Teknos Norge AS.

Statement: *There was an error of field of application in the original extended classification report, the product described in this classification report has not been retested and additional report does not involve technical change or technical review of the original report.*

Prepared by: SIA “Meža un koksnes produktu pētniecības un attīstības institūts” (Forest and Wood Products Research and Development Institute Ltd).

Test performed at: SIA “Meža un koksnes produktu pētniecības un attīstības institūts” (Forest and Wood Products Research and Development Institute Ltd).

Product name: Spruce and pine wood cladding.

Laboratory involved in testing is accredited by the Latvian National Accreditation Bureau (LATAK) according to the standard LVS EN ISO/IEC 17025 under the terms of Latvian legislation with reg. No. T-316. Laboratory is a notified body with reg. No. NB 2040 under construction product regulation No. 305/2011.

Classification report refers only to these test objects. This classification report may not be reproduced otherwise than in full text, excepted with the prior written approval of the Forest and Wood Products Research and Development Institute

1. Introduction

This classification report defines the reaction to fire classification assigned to spruce and pine wood cladding in accordance with the procedures given in EN 13501-1:2018.

2. Details of classified product

2.1. General

Spruce and pine wood cladding is defined as solid wood cladding. Product is described by product standard EN 14915:2013+A2:2020.

2.2. Product description

- Product name: Spruce and pine wood cladding.
- Manufacturer: Teknos Norge AS.
- Materials used for manufacturing:
 - non-impregnated and with Cu impregnated pine and spruce wood with dimensions 19x148 mm;
- Density: $> 400 \text{ kg/m}^3$.
- Nominal thickness tested: 19 mm.
- Coating systems tested for extended application:
 - Primed solid wood cladding, achieved with CU impregnation and primed with opaque Teknol 3881 $\leq 120 \text{ g/m}^2$ wet;
 - Primed and painted solid wood cladding, achieved with CU impregnation and primed with opaque Teknol 3881 $\leq 120 \text{ g/m}^2$ wet and opaque Teknol 3881 $\leq 120 \text{ g/m}^2$ wet;
 - Primed solid wood cladding, primed with opaque Teknol 3890 $\leq 120 \text{ g/m}^2$ wet;
 - Primed solid wood cladding, primed with opaque Teknol 3881 $\leq 120 \text{ g/m}^2$ wet;
 - Primed solid wood cladding, achieved with transparent primer Teknol 1888 $\leq 100 \text{ g/m}^2$ wet;
 - Primed solid wood cladding, achieved with transparent primer Teknol 1830 $\leq 100 \text{ g/m}^2$ wet;
 - Primed and painted solid wood cladding, achieved with transparent primer Teknol 1830 $\leq 100 \text{ g/m}^2$ wet and transparent Nordica Eko 3894 $\leq 150 \text{ g/m}^2$;
 - Stained solid wood cladding, achieved with Teknos Teknoshield 4005 $\leq 90 \text{ g/m}^2$ wet;
 - Primed solid wood cladding, achieved with Teknos Aqua primer 2907-02 $\leq 100 \text{ g/m}^2$ wet;
 - Primed and painted solid wood cladding, achieved with Teknos Aqua primer 2907-02 $\leq 100 \text{ g/m}^2$ wet and Teknos Nordica Eko 3330 $\leq 125 \text{ g/m}^2$ wet;
 - Primed solid wood cladding, achieved with Teknos Aqua primer 2907-42 $\leq 125 \text{ g/m}^2$ wet;
 - Primed and painted solid wood cladding, achieved with Teknos Aqua primer 2907-42 $\leq 125 \text{ g/m}^2$ wet and Teknos Nordica Eko 3894 $\leq 125 \text{ g/m}^2$ wet.

3. Test reports and test results in support of classification

3.1. Specific conditions

Not applicable

3.2. Test reports

Name of laboratory	Name of sponsor	Test reports	Test method
SIA „Meža un koksnes produktu pētniecības un attīstības institūts” Testing Laboratory	Teknos Norge AS	5409-1/2021	EN 13823:2020
SIA „Meža un koksnes produktu pētniecības un attīstības institūts” Testing Laboratory	Teknos Norge AS	5409-2/2021	EN ISO 11925-2:2020

3.3. Test results

Test method	Parameter	Number of tests	Results	
			Continuous parameter mean	Compliance parameters
EN 13823:2020	$FIGRA_{0,2MJ}(W/s)$	3 ^a 15 ^b	671.3	(-)
	$FIGRA_{0,4MJ}(W/s)$		671.3	(-)
	$THR_{600s}(MJ)$		14.1	(-)
	LFS		(-)	Compliant
	$SMOGRA(m^2/s^2)$		3.6 (11.7) ^c	(-)
	$TSP_{600s}(m^2)$		41.9 (86.8) ^c	(-)
EN ISO 11925-2:2020	Flaming droplets <10s	12 72 ^b	(-)	Compliant
	Flaming droplets >10s		(-)	Compliant
	Flame spread (Fs)		(-)	Compliant
	Ignition of filter paper		(-)	Compliant
Exposure time 30 s. Test duration 60 s.	Flaming droplets/particles		(-)	Compliant
(-) not applicable ^a Results of primed with Teknol 1830 Base T (consumption 100 g/m ²) and painted with Nordica Eko 3894-24 (consumption 150 g/m ²) spruce cladding ^b Additional tests results for extended application. ^c Test results from product variation No. 5409-1-8 with worst case scenario for smoke index classification.				

Test results for specimens with additional coatings

Specimen No.	5409-1-1	5409-1-2	5409-1-3	5409-1-4	5409-1-5	5409-1-6	5409-1-7	5409-1-8	5409-1-9	5409-1-10
$FIGRA_{0,2MJ}, W/s$	528.3	623.8	673.8	611.2	560.8	438.9	567.8	706.2	704.6	529.5
$FIGRA_{0,4MJ}, W/s$	528.3	623.8	673.8	611.2	560.8	438.9	567.8	706.2	704.6	529.5
THR_{600s}, MJ	24.3	13.5	16.7	12.9	13.5	16.1	26.2	24.5	26.6	14.1
$SMOGRA, m^2/s^2$	10.8	1.9	2.4	3.0	3.8	3.9	13.1	11.7	11.2	6.6
TSP_{600s}, m^2	67.4	37.1	38.9	31.9	32.1	49.7	56.2	86.8	76.9	55.8
Specimen No.	5409-1-11	5409-1-13	5409-1-15							
$FIGRA_{0,2MJ}, W/s$	555.9	635.1	462.9							
$FIGRA_{0,4MJ}, W/s$	555.9	635.1	462.9							
THR_{600s}, MJ	13.5	14.0	15.0							
$SMOGRA, m^2/s^2$	2.5	3.6	1.8							
TSP_{600s}, m^2	30.6	44.8	37.7							

Specimens identification

Specimen No.	Wood species and area of use	Primer name and consumption	Coating name and consumption
5409-1-1	Stained pine	Teknosshield 4005, 85-90 g/m ²	-
5409-1-2	Primed with rot protection spruce cladding	Aqua 2907-02, 100 g/m ²	-
5409-1-3	Primed with rot protection and coated spruce cladding	Aqua 2907-02, 100 g/m ²	Nordica Eko 3330-12, 125 g/m ²
5409-1-4	Primed with rot protection spruce cladding	Aqua 2907-42, 125 g/m ²	-
5409-1-5	Primed with rot protection and coated spruce cladding	Aqua 2907-42, 125 g/m ²	Nordica Eko 3894, 125 g/m ²
5409-1-6	Untreated spruce cladding	-	-
5409-1-7	CU impregnated pine cladding	-	-
5409-1-8	Primed CU impregnated pine cladding	Teknol 3881, 120 g/m ²	-
5409-1-9	Primed and painted CU impregnated pine	Teknol 3881, 120 g/m ²	Teknol 3881, 120 g/m ²
5409-1-10	Primed spruce cladding	Teknol 3890, 120 g/m ²	-
5409-1-11	Primed spruce cladding	Teknol 3881, 120 g/m ²	-
5409-1-13	Primed spruce cladding	Teknol 1888, 100 g/m ²	-
5409-1-15	Primed spruce cladding	Teknol 1830 Base T, 100 g/m ²	-

4. Classification and field of application

4.1. Reference of classification

This classification has been carried out in accordance with clause 11 of EN 13501-1:2018.

4.2. Classification

Spruce and pine wood cladding in relation to its reaction to fire behaviour is classified:

D

The additional classification in relation to smoke production is:

s2

The additional classification in relation to flaming droplets/particles is:

d0

The format of the reaction to fire classification for construction product excluding floorings and linings is:

Fire behaviour		Smoke production			Flaming droplets	
D	-	s	2	,	d	0

Reaction to fire classification: D-s2, d0

4.3. Field of application

4.3.1 This classification is valid for the following product end use applications:

Product primary is intended to use as solid wood cladding.

4.3.2. This classification is also valid for following product parameters:

- valid for thickness 19 mm and larger thicknesses;
- valid for non-impregnated and with CU impregnated spruce and pine wood;
- valid for wood density $\geq 400 \text{ kg/m}^3$;
- valid with coating systems as tested;
- mounted with ventilated or non-ventilated air gap to substrate of any A1 or A2-s1,d0 and with the air gap constructed by wooden battens of class D-s2,d0 or better or any A1 or A2-s1,d0 product with a minimum density of 525 kg/m^3 ;
- valid for product mounting with air gap between product and substrate. Valid also for product mounting on substrates without air gap;
- valid for product application with standard vertical and horizontal joints;
- valid for vertical and horizontal arrangements;
- valid for all colour tones*.

** According to customer's provided information from extended application report No. PHB10114A about different colour tone influence on reaction to fire performance of paints issued by Danish Institute of Fire and Security Technology (DBI) at Jernholmen 12, DK-2650 Hvidovre, Denmark on 04.12.2020.*

5. Limitations.

5.1. No restrictions on the duration of validity of this classification report as long as the product specifications remain unchanged.

5.2. This document does not represent type approval or certification of the product.

5.3. The classification assigned to the product in this report is appropriate to a declaration of conformity by the manufacturer within the context of system 3 attestation of conformity and CE marking under the Construction Products Regulation.

The manufacturer has made a declaration, which is held on file. This confirms that the product's design requires no specific processes, procedures or stages (e.g. no addition of flame-retardants, limitation of organic content, or addition of fillers) that are aimed at enhancing the fire performance in order to obtain the classification achieved. As a consequence the manufacturer has concluded that system 3 attestation is appropriate.

The test laboratory has, therefore, played no part in sampling the product for the test, although it holds appropriate references, supplied by the manufacturer, to provide for traceability of the samples tested.

Prepared by



E. Bukšāns

(signature and name)

Reviewed by



K. Būmanis

(signature and name)

THIS DOCUMENT IS SIGNED BY SECURE ELECTRONIC SIGNATURE AND CONTAINS A TIME STAMP
(Signature validity can be checked: <https://www.eparaksts.lv/en>)