

www.teknos.com



# **SCOTS PINE**

Botanical name:	Pinus sylvestris, family: PINACEAE
Distribution:	Europe (as far as Asia Minor and Northwest Siberia)
Other important trade names:	Kiefer, Föhre, Nordische Kiefer, Scots pine, redwood, (GB); pin commun (Fr); pino silvestre (It, Sp)

# Abbreviation as per DIN EN 13556: PNSY

# Colour and structure of the wood:

Heartwood brown to red to yellow, no colour stripes. Clear colour contrast between sapwood and heartwood, narrow to medium width (depending on the vigour or the tree age). The sapwood is near white and yellows on exposure to light. The heartwood is yellow to reddish brown and clearly darkens on exposure to light. The dark latewood bands form a clear raised "cathedral effect" formed by innermost growth rings (tangential) on the lateral surfaces or a stripe (radial). Woods with extremely narrow year rings are usually light in colour and appear almost unstructured. Growth zone boundaries clearly recognisable (through the colour contrast between darker latewood and lighter earlywood). The smell of the wood is distinctive (in fresh condition resinous, pleasantly aromatic).

## **Properties:**

Weight fresh [kg/m³]		750 - 820 - 850
Bulk density air-dry (12-15 % u) [g/cm³]	0.51 – 0.55	
Compression strength u12-15 [N/mm <sup>2</sup> ]	45 – 55	
Bending strength u <sub>12-15</sub> [N/mm <sup>2</sup> ]	79 – 100	
Modulus of elasticity (bending) u12-15 [N/mm	11000 – 13000	
Toughness [kJ/m²]		40 - 70
Hardness (BRINELL) $\perp$ to the grain u <sub>12-15</sub> [N/mm <sup>2</sup> ]		14 – 23
Drying shrinkage (fresh up to u <sub>12-15</sub> )	radial [%]	3,0
	tangential [%]	4.5
Differential shrinkage [%/%]	radial	0.15 – 0.19
	tangential	(0.25) – 0.36
pH value (suspension)		5.1
pH value (surface)		4.2
Durability class (EN 350:2016)		DC 3 – 4

## Additional information:

In isolated cases evidence shows that an allergy can be triggered through the resin in hypersensitive persons.



### Workability:

Clear knot-free pinewood is good for sawing, planing, drilling, milling, and nailing; large and loose knots can lead to problems in processing. The wood also can be sliced and cut easily. Resinous wood can stick to tools fast and thus lead to a considerable loss in quality. Nails and screws hold well, even without pre-drilling. Problems in bonding occur in contact with resin and increase with a greater resin content.

### Drying:

Drying generally runs without any problems. It should take place relatively soon after cutting, because pine sapwood is highly susceptible to blue stain fungi in damp condition.

#### Use:

Outdoor or indoor use. Especially suitable for: Outdoor construction with no ground contact (only heartwood), exterior cladding (facades), frame structure (windows, house doors, conservatories), wall and ceiling coverings (internal), furniture, packaging material.





Macroscopic cross-section of pine (10 times magnification lens)

Wood surface of pine (radial section)

## WE MAKE THE WORLD LAST LONGER

The above information is normative and based on laboratory tests and practical experiences. The information is noncommittal, and we cannot accept liability for the results obtained under working conditions beyond our control, and consequently the buyer or the user is not released from the obligation to test the suitability of our products for specific means and application methods under the actual application conditions. Our liability covers only damage caused directly by defects in the products supplied by Teknos. This product is intended for professional use only. This implies that the user possesses sufficient knowledge for using the product correctly with regard to technical and working safety aspects. The latest versions of Teknos' Technical Data Sheets and Safety Data Sheets are available from our homepage <u>www.teknos.com</u>. All trademarks displayed on this document are the exclusive property of Teknos Group or its affiliated companies.



### Surface treatment:

Very resinous wood can lead to discolouring particularly with light coatings. Sapwood is extremely susceptible to fungi and must be protected with deep effect.

## Coating systems:

The coating systems illustrated here are examples developed to ensure utmost durability and lasting quality.

Alternative systems are also available; however, these must be confirmed by Teknos. Please contact your local Teknos representative for further details.

Details on application can be found in the technical data sheets for each product.

## Windows, doors, conservatories, and folding shutters:

System coating	Translucent
Wood preservative*	TEKNOL AQUA 1412-01 / TEKNOL AQUA 1410-01 / TEKNOL AQUA 1415-01
Primer	AQUAPRIMER 2900-X2
Intermediate	AQUAFILLER 6500-01
Topcoat	AQUATOP 2600 translucent topcoat

System coating	Opaque
Wood preservative*	TEKNOL AQUA 1412-01 / TEKNOL AQUA 1410-01 / TEKNOL AQUA 1415-01
Primer	ANTISTAIN AQUA 5200-01
Intermediate	ANTISTAIN AQUA 5200-01
Topcoat	AQUATOP 2600-2X

System coating	Colourless
Wood preservative*	TEKNOL AQUA 1412-01 / TEKNOL AQUA 1410-01 / TEKNOL AQUA 1415-01
Intermediate	AQUAFILLER 6500-01
Topcoat	AQUATOP 2600-6X

\*The use of biocidal products within EU is only allowed if the product has been authorized according to BPR for the country in question. Use biocides safely. Always read the label and product information before use.

## WE MAKE THE WORLD LAST LONGER

The above information is normative and based on laboratory tests and practical experiences. The information is noncommittal, and we cannot accept liability for the results obtained under working conditions beyond our control, and consequently the buyer or the user is not released from the obligation to test the suitability of our products for specific means and application methods under the actual application conditions. Our liability covers only damage caused directly by defects in the products supplied by Teknos. This product is intended for professional use only. This implies that the user possesses sufficient knowledge for using the product correctly with regard to technical and working safety aspects. The latest versions of Teknos' Technical Data Sheets and Safety Data Sheets are available from our homepage <u>www.teknos.com</u>. All trademarks displayed on this document are the exclusive property of Teknos Group or its affiliated companies.



#### Wood is a unique, beautiful, and very versatile material

The features and properties of wood vary greatly and therefore individual attention is required in processing and surface finishing.

With this Teknos wood data sheet we would like to go into detail on the features and range of applications in the coating of important wood species.

The data sheet originated from a collaboration with the Johann Heinrich von Thünen-Institute in Hamburg.

The pH values of wood have been determined as important chemical variables for the first time.

The concentration dependence of extracts such as tannic acids or tannins to the pH value is important.

A good surface coating and targeted selection of system structures shall be safer based on these variables determined by Thünen-Institute and demonstrate wood-related problem solving.

All system structures named in the data sheet are selected according to utmost durability and quality and are considered to be relevant systems. However, a practical test is always necessary.

Due to different application possibilities and stresses of parts to be coated, variations are required.

To select individual systems easily, the Teknos technical department will be happy to assist you.

## WE MAKE THE WORLD LAST LONGER

The above information is normative and based on laboratory tests and practical experiences. The information is noncommittal, and we cannot accept liability for the results obtained under working conditions beyond our control, and consequently the buyer or the user is not released from the obligation to test the suitability of our products for specific means and application methods under the actual application conditions. Our liability covers only damage caused directly by defects in the products supplied by Teknos. This product is intended for professional use only. This implies that the user possesses sufficient knowledge for using the product correctly with regard to technical and working safety aspects. The latest versions of Teknos? Technical Data Sheets and Safety Data Sheets are available from our homepage www.teknos.com. All trademarks displayed on this document are the exclusive property of Teknos Group or its affiliated companies.