

5.5.2021

1 (1)

Teknos Oy P.o.Box.107 00371 Helsinki

Replaces Customer report VTT-CR-01512-20

The following coating system for concrete constructions has been tested by VTT (Technical research centre of Finland) according to the following instructions and standards:

- STUK-YTO-TR-210 2017. Requirements for coatings of nuclear power plant containments.
- ASTM D 3911 16, 2016. Standard test method for evaluating coatings used in lightwater nuclear power plants at simulated design basis accident (DBA) conditions.
- ASTM D 4082 10, 2010. Standard test method for effects of gamma radiation on coatings for use in nuclear power plants. *
- ISO 8690, 1988. Decontamination of radioactively contaminated surfaces Method of testing and assessing the ease of decontamination.

Coating system

TEKNOFLOOR AQUA 110F A,

3 x 60 µm

Total DFT

180 µm

Manufacturer

Teknos Ov

According to test results, this coating system fulfils the requirements given in 2017 by Radiation and Nuclear Safety authority of Finland (STUK) for Radiation (gamma) and DBA-resistance and Ease of decontamination. Full experimental details have been given in report VTT-R-00256-20.

*) The total accumulated dose was 1×10^8 rads (= 1×10^6 J/kg = 1×10^6 Gy) and the dose rates were greater than the regulator required.

Espoo, 5.5.2021

Pasi Vaisanun
7CB4882A118A42C...

Pasi Väisänen

Engineer

DocuSigned by:

Sami Penttilä

Research Team Leader