



HYDROPUR 2K COLOR

WATER-BORNE 2K COLORED COATING

IDEAL FOR PVC & GRP WINDOWS & DOORS

The high-quality colored coating was specially developed for use on PVC and GRP surfaces in interior and exterior situations. HYDROPUR 2K COLOR excels through its excellent weather resistance, light fastness and surface filling properties. The product's good resistance and quick drying properties make it ideal for application as a single-layer coating on PVC and GRP windows and doors. Overcoating with HYDROPUR 2K 7590 clearcoat is possible and achieves an even higher quality of surface finish.

COATINGS INSTEAD OF FILMS

In contrast to film, a coating offers all kinds of advantages: from flexibility in the amounts ordered right up to ease of maintenance. The top coat adheres not only to PVC profiles and co-extruded seals but also to mixed forms of construction.

CONTACT US

Calling Teknos is a quick and easy way to get expert advice on the use of HYDROPUR 2K COLOR or other Teknos coating products. Our technical customer service is always at your disposal when it comes to developing optimum coating solutions and systems.

MAIN FEATURES

High weather resistance, light fastness and long-term elasticity

Also available as a textured coating

Ideal for PVC & GRP:
suitable for interior or exterior use

Scratches and other damage are easily rectified

Cost-effective alternative to film

Customer-specific effect coatings and customised colors available



Our mission is to extend the life of your products by providing intelligent, technically advanced paint and coating solutions for even better protection - always in close collaboration with our customers.



PRODUCT FACTS

HYDROPUR 2K COLOR

WATER-BORNE 2K COLORED COATING

VERSIONS	HYDROPUR 2K COLOR 7515-20 HYDROPUR 2K COLOR 7515-30 HYDROPUR 2K COLOR 7516-15 STRUKTUR
COLOURS	RAL and NCS S colour cards
GLOSS LEVEL	Colored coating: Satin 20, Satin 30 Texture: Matt 15
APPLICATION	<ul style="list-style-type: none">▪ Gravity feed gun▪ Airless (airmix) spraying
CONTAINER SIZE	<ul style="list-style-type: none">▪ Paint: 2.47 L, 8.2 L▪ Hardener: 1 kg, 5 kg
MIXING RATIO	10:1 by weight

DRYING TIMES	
Dust dry after	30 minutes
Touch dry after	90 minutes
Sandable after	3 hours
Recoat after	3 hours
Fully dry after	24 hours

Note: Chemically resistant after 14 days


COATING RECOMMENDATION

PVC/GRP	HYDROPUR 2K COLOR 7515	HYDROPUR 2K COLOR 7516 STRUKTUR
SURFACE PREPARATION	Cleaning with REINIGUNGSMITTEL 1530-98	Cleaning with REINIGUNGSMITTEL 1530-98
FIRST COAT	HYDROPUR 2K COLOR 7515	HYDROPUR 2K COLOR 7516 STRUKTUR

For further technical information refer to data sheet no. 7515

TESTS

- High weather resistance at an overall radiation load of $\geq 10 \text{ GJ/m}^2$ (DIN EN 513)
- Complies with the VOC and "Decopaint" Directive 2010
- No special labelling requirements



WE MAKE THE WORLD LAST LONGER

TEKNOS GROUP OY
Takkatie 3
P.O. Box 107
FI-00370 Helsinki
T +358 9 506 091
sales@teknos.com

www.teknos.com

