

Teknos Norge AS
Industriveien 28
3430 Spikkestad

Reaction to fire classification report

1 Introduction

This classification report defines the classification assigned to the product “Forestia Chipboard + Teknosafe 2457” in accordance with the procedure given in EN 13501-1:2007+A1:2009.

2 Details of classified product

2.1 General

The product “Forestia Chipboard + Teknosafe 2457” is defined as a coated wooden particle board system. Its classification is valid for the following end use applications:

According to the owner of this classification report, this product complies with the European product specification EN 13986.

2.2 Product description

The product, “Forestia Chipboard + Teknosafe 2457”, is fully described below:

Coated wooden fibre board system, consisting of a core of “Forestia Chipboard”, nominal thickness 12 mm and nominal density 700 kg/m³. The facing of the product is coated with a FR-paint called “Teknosafe 2457”, nominal area weight of 250 – 300 g/m² (wet weight).

3 Test reports & test results in support of classification

3.1 Test reports

This classification is based on the test report listed below:

Name of laboratory	Name of sponsor	Test report ref no	Accredited test method
SP	Teknos Norge AS	6P00077	EN 13823 and EN ISO 11925-2

SP Technical Research Institute of Sweden

Postal address
SP
Box 857
SE-501 15 BORÅS
Sweden

Office location
Västeråsen
Brinellgatan 4
SE-504 62 BORÅS

Phone / Fax / E-mail
+46 10 516 50 00
+46 33 13 55 02
info@sp.se

Laboratories are accredited by the Swedish Board for Accreditation and Conformity Assessment (SWEDAC) under the terms of Swedish legislation. This report may not be reproduced other than in full, except with the prior written approval of the issuing laboratory.

3.2 Test results

Test method	Parameter	Number of tests	Results	
			Continuous parameter mean (m)	Compliance with parameters
EN ISO 11925-2		12		
Edge/Surface flame attack**				
30 s exposure	$F_s \leq 150$ mm		(-)	Compliant
Flaming droplets/particles	Ignition of filter paper		(-)	No ignition of filter paper
EN 13823		3		
	$FIGRA_{0,2MJ}$ (W/s)		61	Compliant
	$FIGRA_{0,4MJ}$ (W/s)		61	Compliant
	$LFS < \text{edge}$		(-)	Compliant
	THR_{600s} , (MJ)		6.6	Compliant
	$SMOGRA$, (m^2/s^2)		1	Compliant
	TSP_{600s} , (m^2)		36	Compliant
	Flaming droplets/particles		(-)	No flaming droplets/particles

** : as required to the end use application of the product

(-) : not applicable

4 Classification and field of application

4.1 Reference and direct field of application

This classification has been carried out in accordance with clause 11 and 15 of EN 13501-1:2007+A1:2009.

4.2 Classification

The product called “Forestia Chipboard + Teknosafe 2457” in relation to its reaction to fire behaviour is classified:

B

The additional classification in relation to smoke production is:

s1

The additional classification in relation to flaming particles/droplets is:

d0

The format of the reaction to fire classification for construction products excluding floorings and linear pipe thermal insulation product is:

Fire Behaviour		Smoke Production			Flaming Droplets	
B	-	s	1	,	d	0

Reaction to fire classification: *B-s1,d0*

4.3 Field of application:

This classification is valid for the following product parameters:

Wooden fibre board “Forestia Chipboard”.

Nominal thickness: 12 mm.

Nominal density: 700 kg/m³.

Paint system consisting of the following layers, applied on the wooden fibre board.

Coating (Teknosafe 2457): nominal amount, 250 – 300 g/m² (wet weight).

Maximum organic content in coating specified as TOP-NCS-S0540Y20R / AV – 57.3 ml / 0.9 liter.

This classification is valid for the following end use conditions:

Substrates

- Wood based substrates at least 10 mm thick and any end use substrate of Euroclasses A1 or A2-s1,d0 at least 9 mm thick, having a density $\geq 510 \text{ kg/m}^3$.

Fixings

- Joints glued with PVAc adhesive.
- Mechanically fixed.

Joints

- Horizontal and vertical joints.

5 Limitations

This classification document does not represent type approval or certification of the product.

SP Technical Research Institute of Sweden Fire Research - Fire Dynamics

Performed by

Examined by

Richard Johansson

Per Thureson