

TECHNICAL DATASHEET

Description : **TEKNOLUX AQUA PRIMER 240**

Product Number : **471-240-0000**

Description : Colourless waterborne UV-curable insulation coat with good transfer efficiency suitable for soft roller application. This product promotes 'aesthetic' warm looks, excellent adhesion on wood substrates as well as provides a barrier effect avoiding the penetration of reactive diluents from UV sealers into wood. It can be used as stain base tinted with TEKNOS pigment paste series.

Characteristics

Viscosity : 5 - 25 sec. in DIN 6mm at 25°C
Density : 1.04 ± 0.02 kg/l
Solid Content : 30 - 35%
VOC : Max 3%
Classification : Complies with the Environmental Protection Act of 1990.

Application

Preparation : Stir well and check before use.
Hardener : Not applicable
Thinner : Not required
Viscosity : As delivered
Film Weight : Apply 10 - 15 g/m².
Mode : Apply in soft roller machine.
Curing : Semi-cure: 60 - 70 mJ/cm²
Surface cure: 190 - 200 mJ/cm²
Drying : 1 - 3 minutes at 40°C - 50°C circulatory air or ventilated air followed by IR exposure. UV-curing should follow after oven drying with all water have been released. (Depend on the coating thickness applied)

TECHNICAL DATASHEET

Description : **TEKNOLUX AQUA PRIMER 240**

Product Number : **471-240-0000**

Substrate : This product is specially formulated to promote adhesion to wood substrate and to TEKNOS UV-curable sealers. Please consult our technical staff prior to other applications.

Storage

Shelf Life : 6 months

Conditions : Protect from sunlight and frost. Keep container tightly closed and in a well ventilated place. Keep away from sources of ignition, heat and oxidizing substances.

To be stored at 5 - 35 °C.

Delivery

Packaging : Available in 20 kg pails.

Delivery Time : Please allow 6 working days of production and transportation.

Cleaning : Clean equipment with water immediately after use.

Precautions : Refer to Safety Data Sheet.

Health & Safety : Refer to Safety Data Sheet.