

TECHNICAL DATASHEET

Description : **UV FILLER**
Product Number : **611-993-0570**

Description : Pigmented acrylic white UV curable filler for roller application in the coating process of solid wood and fiberboards for doors, kitchen cabinets and furniture.

Characteristics

Viscosity : 100 - 130 dPa.s in Dynamic measurement (#2) at 25°C.
Density : 1.74 ± 0.02 kg/l
Solid Content : 98 - 99%
VOC : Max 2%
Pigments : Does not contain any lead, cadmium or chromate.
Classification : Complies with the Environmental Protection Act of 1990.

Application

Preparation : Stir well and check before use.
Hardener : Not required
Thinner : Not required
Viscosity : As delivered
Film Weight : Apply 15 - 35 g/m².
Mode : Apply in roller machine.
Curing : Semi cure: 70 - 80 mJ/cm²
Full cure: 195 - 205 mJ/cm²

Substrate : This product is specially formulated as filler to be applied on wood substrates with high porosity. Please consult our technical staff prior to other applications.

TECHNICAL DATASHEET

Description : UV FILLER
Product Number : 611-993-0570

Storage

Shelf Life : 12 months
Conditions : The product should be stored between 5°C and 35°C. Keep container tightly closed and in a well ventilated place. Keep away from sources of ignition, heat and oxidizing substances. Higher temperatures reduce the shelf life. Protect from sunlight and frost.

Delivery

Packaging : Available in 20 kg pails.
Delivery Time : Please allow 6 working days of production and transportation.

Cleaning : Use solvent such as butyl acetate for cleaning.

Precautions : Refer to Safety Data Sheet.

Health & Safety : Refer to Safety Data Sheet.