

TECHNICAL DATASHEET

Description : **UV TOPCOAT**

Product Number : **651-993-0760**

Description : Colourless acrylic UV-curable topcoat for roller application in direct coating / printing process of fiberboards and particleboards. This product comprises various finishes producing special decorative effects as well as protecting the substrate from chemical and mechanical impacts.

Characteristics

Viscosity : 30 - 50 sec. in DIN 6mm at 25°C

Density : 1.2 ± 0.02 kg/l

Solid Content : 98 - 99%

VOC : Max 1 - 2%

Classification : Complies with the Environmental Protection Act of 1990.

Application

Preparation : Stir well and check before use.

Hardener : Not required

Thinner : Not required

Viscosity : As delivered

Film Weight : Apply 8 - 12 g/m².

Mode : Apply in roller machine.

Curing : Semi cure: 70 - 80 mJ/cm²
Full cure: 190 - 210 mJ/cm²

Substrate : The product is specially formulated as topcoat to be applied on TEKNOS UV-Curable sealer. Please consult our technical staff prior to other applications.

Storage

TECHNICAL DATASHEET

Page: 2 / 2

Description : **UV TOPCOAT**

Product Number : **651-993-0760**

Shelf Life : 6 months

Conditions : The product should be stored between 5°C and 35°C. Keep container tightly closed and in a well ventilated place. Keep away from sources of ignition, heat and oxidizing substances. Higher temperatures reduce the shelf life. Protect from sunlight and frost.

Delivery

Packaging : Available in 20 kg pails.

Delivery Time : Please allow 6 working days of production and transportation.

Cleaning : Use solvent such as butyl acetate for cleaning.

Precautions : Refer to Safety Data Sheet.

Health & Safety : Refer to Safety Data Sheet.