TEKNOS (M) Sdn. Bhd. (formerly known as Teknos Treffert (M) Sdn.

Bhd.)

PLO 577, Jalan Keluli 8 Kawasan Perindustrian Pasir Gudang 81700 Pasir Gudang, Johor, Malaysia T +60 7 251 5115 F +60 7 251 4115 info.malaysia@teknos.com www.teknos.my



TECHNICAL DATASHEET

Page: 1 / 2

Description : MUV SEALER
Product Number : 661-209-0002

Description : Acrylic UV-curable sealer for roller application in the coating process

of PDL thin board and / or furniture panels. The product shows excellent adhesion, sealing, leveling properties and give matt finish.

Characteristics

Viscosity: 40 sec. in DIN 6mm at 25°C

Density : $1.39 \pm 0.02 \text{ kg/l}$

Solid Content : 98-99% VOC : Max 3%

Classification : Complies with the Environmental Protection Act of 1990.

Application

Preparation : Stir well and check before use.

Hardener : Not requiredThinner : Not requiredViscosity : As delivered

Film Weight : Apply 15-20 g/m².

Mode : Apply in roller machine with a shore hardness of offset rollers of 40-

50 (Isobutylene / Isoprene-Copolymer or EPDM-Prepolymer).

Curing : Semi-cure: 70-80 mJ/cm²

Surface cure: 190-200 mJ/cm²

Substrate : The product is specially formulated as UV sealer to be applied on

TEKNOS coating UV Filler or duro sealer. The product provides excellent support to TEKNOS Coatings 651-/652 UV- Top coat.

Please consult our technical staff prior to other applications.

Storage

TEKNOS (M) Sdn. Bhd. (formerly known as Teknos Treffert (M) Sdn. Bhd.) PLO 577, Jalan Keluli 8 Kawasan Perindustrian Pasir Gudang

81700 Pasir Gudang, Johor, Malaysia

T +60 7 251 5115 F +60 7 251 4115 info.malaysia@teknos.com www.teknos.my



TECHNICAL DATASHEET

Page: 2 / 2

Description : MUV SEALER
Product Number : 661-209-0002

Shelf Life : 6 months

Conditions : Protect from sunlight and frost. Keep container tightly closed and in

a well ventilated place. Keep away from sources of ignition, heat and

oxidizing substances.

To be stored at 5-35 °C.

Delivery

Packaging : Available in 20 kg pails.

Delivery Time : Please allow 6 working days of production and transportation.

Quantity : Except for trial, minimum quantity is 100kg per individual product.

Cleaning : Use solvent such as butyl acetate for cleaning.

Precautions : Refer to Safety Data Sheet.

Health & Safety : Refer to Safety Data Sheet.