TEKNOS (M) Sdn. Bhd. PLO 577, Jalan Keluli 8 Kawasan Perindustrian Pasir Gudang 81700 Pasir Gudang, Johor, Malaysia T +60 7 251 5115 F +60 7 251 4115 info.malaysia@teknos.com www.teknos.my



TECHNICAL DATASHEET

Page: 1 / 2

Description : UVILUX DURO SEALER 240

Product Number : 661-240-0000

Description : Colorless acrylic UV-curable sealer for roller application coating process of parquet and veneered flooring panels. The UV sealer exhibits good hardness and excellent abrasion resistance that is suitable for residential applications. Product contains Alox.

Characteristics		
Viscosity	:	80 - 100 sec. in DIN 8mm at 25°C
Density	:	1.4 ± 0.02 kg/l
Solid Content	:	98 - 99%
VOC	:	Max 2%
Classification	:	Complies with the Environmental Protection Act of 1990.
Amaliantina		
Application		
Preparation	:	Stir well and check before use.
Hardener	:	Not required
Thinner	:	Not required
Viscosity	:	As delivered
Film Weight	:	Apply 30 - 60 g/m ² .
Mode	:	Apply in roller machine.
Curing	:	Semi cure: 70 - 80 mJ/cm ² Full cure: 190 - 200 mJ/cm ²
Substrate	:	The product is a specially formulated UV sealer to be applied on TEKNOS UV filler or sealer. The product provides abrasion support to TEKNOS UV Topcoat. Please consult our technical staff prior to

The information in this datasheet is given to the best of our ability based on our laboratory results. As we have no control over the quality of substrate nor the application conditions and methods used, we recommend the user to test the product for the purpose required. We are not liable for any compensation nor damages arising due to improper use of our products. The information contained herein is subject to change without further notice. This leaflet is invalid when it is replaced by a newer version.

other applications.

TEKNOS (M) Sdn. Bhd. PLO 577, Jalan Keluli 8 Kawasan Perindustrian Pasir Gudang 81700 Pasir Gudang,Johor, Malaysia T +60 7 251 5115 F +60 7 251 4115 info.malaysia@teknos.com www.teknos.my



TECHNICAL DATASHEET

Page: 2 / 2

Description	:	UVILUX DURO SEALER 240
Product Number	:	661-240-0000

Storage

•	
Shelf Life	: 6 months
Conditions	: The product should be stored between 5°C and 35°C. Keep container tightly closed and in a well ventilated place. Keep away from sources of ignition, heat and oxidizing substances. Higher temperatures reduce the shelf life. Protect from sunlight and frost.

Delivery		
Packaging	:	Available in 20 kg pails.
Delivery Time	:	Please allow 6 working days of production and transportation.
Cleaning	:	Use solvent such as butyl acetate for cleaning.
Precautions	:	Refer to Safety Data Sheet.
Health & Safety	:	Refer to Safety Data Sheet.