TEKNOS (M) Sdn. Bhd. (formerly known as Teknos Treffert (M) Sdn.

Bhd.) PLO 577, Jalan Keluli 8

Kawasan Perindustrian Pasir Gudang 81700 Pasir Gudang, Johor, Malaysia T +60 7 251 5115 F +60 7 251 4115 info.malaysia@teknos.com www.teknos.my



TECHNICAL DATASHEET

Page: 1 / 2

Description : UVILUX DURO SEALER 240

Product Number : 661-240-0000

Description : Colorless acrylic UV-curable sealer for roller application coating

process of parquet and veneered flooring panels. The UV sealer exhibits good hardness and excellent abrasion resistance that is

suitable for residential applications. Product contains Alox.

Characteristics

Viscosity : 80 - 100 sec. in DIN 8mm at 25°C

Density : $1.4 \pm 0.02 \text{ kg/l}$

Solid Content : 98 - 99% VOC : Max 2%

Classification : Complies with the Environmental Protection Act of 1990.

Application

Preparation : Stir well and check before use.

Hardener : Not requiredThinner : Not requiredViscosity : As delivered

Film Weight : Apply 30 - 60 g/m².

Mode : Apply in roller machine.

Curing : Semi cure: 70 - 80 mJ/cm²

Full cure: 190 - 200 mJ/cm²

Substrate : The product is a specially formulated UV sealer to be applied on

TEKNOS UV filler or sealer. The product provides abrasion support to TEKNOS UV Topcoat. Please consult our technical staff prior to

other applications.

TEKNOS (M) Sdn. Bhd. (formerly known as Teknos Treffert (M) Sdn. Bhd.) PLO 577, Jalan Keluli 8

Kawasan Perindustrian Pasir Gudang 81700 Pasir Gudang, Johor, Malaysia T +60 7 251 5115 F +60 7 251 4115 info.malaysia@teknos.com www.teknos.my



TECHNICAL DATASHEET

Page: 2 / 2

Description : UVILUX DURO SEALER 240

Product Number : 661-240-0000

Storage

Shelf Life : 6 months

Conditions : Protect from sunlight and frost. Keep container tightly closed and in

a well ventilated place. Keep away from sources of ignition, heat and

oxidizing substances.

To be stored at 5 - 35 °C.

Delivery

Packaging : Available in 20 kg pails.

Delivery Time : Please allow 6 working days of production and transportation.

Cleaning : Use solvent such as butyl acetate for cleaning.

Precautions : Refer to Safety Data Sheet.

Health & Safety : Refer to Safety Data Sheet.