

TECHNICAL DATASHEET

Description : **UVILUX DURO SEALER 260**

Product Number : **661-260-0000**

Description : Colorless acrylic UV-curable sealer for roller application coating process of parquet. The UV sealer exhibits excellent hardness and abrasion resistance suitable for commercial applications. Product contains Alox.

Characteristics

Viscosity : 55 - 65 sec. in DIN 8mm at 25°C

Density : 1.4 ± 0.02 kg/l

Solid Content : 98 - 99%

VOC : Max 2%

Classification : Complies with the Environmental Protection Act of 1990.

Application

Preparation : Stir well and check before use.

Hardener : Not required

Thinner : Not required

Viscosity : As delivered

Film Weight : Apply 20 - 60 g/m².

Mode : Apply in roller machine.

Curing : Semi cure: 70 - 80 mJ/cm²
Full cure: 200 - 210 mJ/cm²

Substrate : The product is a specially formulated UV sealer to be applied on TEKNOS UV filler or sealer. The product provides abrasion support to TEKNOS UV Topcoat. Please consult our technical staff prior to other applications.

TECHNICAL DATASHEET

Page: 2 / 2

Description : **UVILUX DURO SEALER 260**
Product Number : **661-260-0000**

Storage

Shelf Life : 6 months
Conditions : The product should be stored between 5°C and 35°C. Keep container tightly closed and in a well ventilated place. Keep away from sources of ignition, heat and oxidizing substances. Higher temperatures reduce the shelf life. Protect from sunlight and frost.

Delivery

Packaging : Available in 20 kg pails.
Delivery Time : Please allow 6 working days of production and transportation.

Cleaning : Use solvent such as butyl acetate for cleaning.

Precautions : Refer to Safety Data Sheet.

Health & Safety : Refer to Safety Data Sheet.