

# TECHNICAL DATASHEET

Page: 1 / 2

**Description** : **UVILUX DURO SEALER 260**  
**Product Number** : **661-260-0000**

**Description** : Colorless acrylic UV-curable sealer for roller application coating process of parquet. The UV sealer exhibits excellent hardness and abrasion resistance suitable for commercial applications. Product contains Alox.

## Characteristics

*Viscosity* : 55 - 65 sec. in DIN 8mm at 25°C  
*Density* :  $1.4 \pm 0.02$  kg/l  
*Solid Content* : 98 - 99%  
*VOC* : Max 2%  
*Classification* : Complies with the Environmental Protection Act of 1990.

## Application

*Preparation* : Stir well and check before use.  
*Hardener* : Not required  
*Thinner* : Not required  
*Viscosity* : As delivered  
*Film Weight* : Apply 20 - 60 g/m<sup>2</sup>.  
*Mode* : Apply in roller machine.  
*Curing* : Semi cure: 70 - 80 mJ/cm<sup>2</sup>  
Full cure: 200 - 210 mJ/cm<sup>2</sup>

**Substrate** : The product is a specially formulated UV sealer to be applied on TEKNOS UV filler or sealer. The product provides abrasion support to TEKNOS UV Topcoat. Please consult our technical staff prior to other applications.

## TECHNICAL DATASHEET

Page: 2 / 2

**Description** : UVILUX DURO SEALER 260  
**Product Number** : 661-260-0000

### Storage

**Shelf Life** : 6 months  
**Conditions** : Protect from sunlight and frost. Keep container tightly closed and in a well ventilated place. Keep away from sources of ignition, heat and oxidizing substances.  
  
To be stored at 5 - 35 °C.

### Delivery

**Packaging** : Available in 20 kg pails.  
**Delivery Time** : Please allow 6 working days of production and transportation.

**Cleaning** : Use solvent such as butyl acetate for cleaning.

**Precautions** : Refer to Safety Data Sheet.

**Health & Safety** : Refer to Safety Data Sheet.