

TECHNICAL DATASHEET

Description : **UVILUX SEALER 239**

Product Number : **661-239-0000**

Description : Alox-free acrylic UV-curable sealer for roller application for flooring. The UV sealer shows good sealing property and good hardness.

Characteristics

Viscosity : 65 - 75 sec. in DIN 8mm at 25°C

Density : 1.18 ± 0.02 kg/l

Solid Content : 98 - 99%

VOC : Max 2%

Classification : Complies with the Environmental Protection Act of 1990.

Application

Preparation : Stir well and check before use.

Hardener : Not required

Thinner : Not required

Viscosity : As delivered

Film Weight : Apply 20 - 30 g/m².

Mode : Apply in roller machine.

Curing : Semi cure: 70 - 80 mJ/cm²
Full cure: 190 - 200 mJ/cm²

Substrate : The product is a specially formulated as UV sealer to be applied on TEKNOS UV fillers or durosealers. The product provides excellent support to Teknos UV Topcoats. Please consult our technical staff prior to other applications.

Storage

TECHNICAL DATASHEET

Description : **UVILUX SEALER 239**

Product Number : **661-239-0000**

Shelf Life : 6 months

Conditions : The product should be stored between 5°C and 35°C. Keep container tightly closed and in a well ventilated place. Keep away from sources of ignition, heat and oxidizing substances. Higher temperatures reduce the shelf life. Protect from sunlight and frost.

Delivery

Packaging : Available in 20 kg pails.

Delivery Time : Please allow 6 working days of production and transportation.

Cleaning : Use solvent such as butyl acetate for cleaning.

Precautions : Refer to Safety Data Sheet.

Health & Safety : Refer to Safety Data Sheet.