TEKNOS (M) Sdn. Bhd. (formerly known as Teknos Treffert (M) Sdn.

Bhd.)

PLO 577, Jalan Keluli 8

Kawasan Perindustrian Pasir Gudang 81700 Pasir Gudang, Johor, Malaysia T +60 7 251 5115 F +60 7 251 4115 info.malaysia@teknos.com www.teknos.my



TECHNICAL DATASHEET

Page: 1 / 2

Description : UVILUX SEALER 239

Product Number : 661-239-0000

Description : Alox-free acrylic UV-curable sealer for roller application for flooring.

The UV sealer shows good sealing property and good hardness.

Characteristics

Viscosity : 65 - 75 sec. in DIN 8mm at 25°C

Density : $1.18 \pm 0.02 \text{ kg/l}$

Solid Content : 98 - 99% VOC : Max 2%

Classification : Complies with the Environmental Protection Act of 1990.

Application

Preparation : Stir well and check before use.

Hardener : Not requiredThinner : Not requiredViscosity : As delivered

Film Weight : Apply 20 - 30 g/m².

Mode : Apply in roller machine.

Curing : Semi cure: 70 - 80 mJ/cm²

Full cure: 190 - 200 mJ/cm²

Substrate : The product is a specially formulated UV sealer to be applied on

TEKNOS UV fillers or sealers. Please consult our technical staff prior

to other applications.

Storage

Shelf Life : 6 months

The information in this datasheet is given to the best of our ability based on our laboratory results. As we have no control over the quality of substrate nor the application conditions and methods used, we recommend the user to test the product for the purpose required. We are not liable for any compensation nor damages arising due to improper use of our products. The information contained herein is subject to change without further notice. This leaflet is invalid when it is replaced by a newer version. Please ask for the latest version.

TEKNOS (M) Sdn. Bhd. (formerly known as Teknos Treffert (M) Sdn. Bhd.) PLO 577, Jalan Keluli 8 Kawasan Perindustrian Pasir Gudang

81700 Pasir Gudang, Johor, Malaysia

T +60 7 251 5115 F +60 7 251 4115 info.malaysia@teknos.com www.teknos.my



TECHNICAL DATASHEET

Page: 2 / 2

Description : UVILUX SEALER 239

Product Number : 661-239-0000

Conditions : Protect from sunlight and frost. Keep container tightly closed and in

a well ventilated place. Keep away from sources of ignition, heat and

oxidizing substances.

To be stored at 5 - 35 °C.

Delivery

Packaging : Available in 20 kg pails.

Delivery Time : Please allow 6 working days of production and transportation.

Cleaning : Use solvent such as butyl acetate for cleaning.

Precautions: Refer to Safety Data Sheet.

Health & Safety : Refer to Safety Data Sheet.