TEKNOS (M) Sdn. Bhd.
(formerly known as Teknos Treffert (M) Sdn. Bhd.)
PLO 577, Jalan Keluli 8
Kawasan Perindustrian Pasir Gudang
81700 Pasir Gudang,Johor, Malaysia

T +60 7 251 5115
F +60 7 251 4115
info.malaysia@teknos.com
www.teknos.my

TEKNOS

TECHNICAL DATASHEET

Description	:	**UVILUX SEALER 244**
Product Number	:	**661-244-0000**

Description	:	Colourless acrylic UV-curable sealer for roller application in the coating process of parquet and veneered flooring panels. The product shows good sandability and sealing property.

Characteristics

Viscosity	:	70 - 80 sec. in DIN 8mm at 25°C
Density	:	1.3 ± 0.2 kg/l
Solid Content	:	98 - 99%
VOC	:	Max 2%
Classification	:	Complies with the Environmental Protection Act of 1990.

Application

Preparation	:	Stir well and check before use.
Hardener	:	Not required
Thinner	:	Not required
Viscosity	:	As delivered
Film Weight	:	Apply 12 - 18 g/m^2.
Mode	:	Apply in roller machine.
Curing	:	Semi cure: 70 - 80 mJ/cm^2 Full cure: 190 - 200 mJ/cm^2

Substrate	:	The product is a specially formulated UV sealer to be applied on TEKNOS UV fillers or sealers. Please consult our technical staff prior to other applications.

TEKNOS

TECHNICAL DATASHEET

Description	:	**UVILUX SEALER 244**
Product Number	:	**661-244-0000**

Storage

Shelf Life	:	6 months
Conditions	:	Protect from sunlight and frost. Keep container tightly closed and in a well ventilated place. Keep away from sources of ignition, heat and oxidizing substances. To be stored at 5 - 35 ^{O}C.

Delivery

Packaging	:	Available in 20 kg pails.
Delivery Time	:	Please allow 6 working days of production and transportation.

Cleaning	:	Use solvent such as butyl acetate for cleaning.
Precautions	:	Refer to Safety Data Sheet.
Health & Safety	:	Refer to Safety Data Sheet.