TEKNOS TREFFERT (M) Sdn. Bhd. T + 60.7 251 5115 (formerly known as Treffert Coatings (S.E.A.) F + 60.7 251 4115

Sdn. Bhd.) PLO 577, Jalan Keluli 8

Kawasan Perindustrian Pasir Gudang 81700 Pasir Gudang, Johor, Malaysia T +60 7 251 5115 F +60 7 251 4115 info.malaysia@teknos.com

www.teknos.my



TECHNICAL DATASHEET

Page: 1 / 2

Description : HPC ANTI SCRATCH TOPCOAT (REV)

Product Number : 651-240-3000

Description : Anti-scratch acrylic UV-curable topcoat for reversable-roller

application in the coating process of triply parquet, solid wood parquet and veneered flooring panels. Compared to conventional topcoats, the product shows significant improvement in the scratch resistance caused by hard particles or materials. The anti-scratch topcoat does not show any abrasive effect and therefore it is

sandable and recoatable.

Characteristics

Viscosity : 27 - 33 sec. in DIN 6mm at 25°C

Density : $1.16 \pm 0.02 \text{ kg/l}$

Solid Content : 98 - 99% VOC : Max 2%

Classification : Complies with the Environmental Protection Act of 1990.

Application

Preparation : Stir well and check before use.

Hardener: Not requiredThinner: Not requiredViscosity: As delivered

Film Weight : Apply 8 - 12 g/m².

Mode : Apply in roller machine with a shore hardness of offset rollers of 40-

50 (Isobutylene / Isoprene-Copolymer or EPDM-Prepolymer).

Curing : Semi cure: 80 - 90 mJ/cm²

Full cure: 270 - 280 mJ/cm²

Substrate : The product is specially formulated as topcoat to be applied on

TEKNOS TREFFERT-COATINGS 661- UV-Curable sealer/ 662- UV-Curtain sealer. Please consult our technical staff prior to other

TEKNOS TREFFERT (M) Sdn. Bhd. (formerly known as Treffert Coatings (S.E.A.) F +60 7 251 4115

Sdn. Bhd.)

PLO 577, Jalan Keluli 8 Kawasan Perindustrian Pasir Gudang 81700 Pasir Gudang, Johor, Malaysia

T+60 7 251 5115 info.malaysia@teknos.com

www.teknos.my



TECHNICAL DATASHEET

Page: 2 / 2

Description : HPC ANTI SCRATCH TOPCOAT (REV)

Product Number : 651-240-3000

applications.

Storage

Shelf Life : 6 months

Conditions : Protect from sunlight and frost. Keep container tightly closed and in

a well ventilated place. Keep away from sources of ignition, heat and

oxidizing substances.

To be stored at 5 - 35 °C.

Delivery

: Available in 20 kg pails. Packaging

Delivery Time Please allow 6 working days of production and transportation.

Quantity Minimum quantity is 20 kg.

Cleaning Use solvent such as butyl acetate for cleaning.

Precautions Refer to Safety Data Sheet.

Health & Safety : Refer to Safety Data Sheet.