TEKNOS (M) Sdn. Bhd. PLO 577, Jalan Keluli 8

Kawasan Perindustrian Pasir Gudang 81700 Pasir Gudang, Johor, Malaysia T +60 7 251 5115 F +60 7 251 4115

info.malaysia@teknos.com www.teknos.my



## TECHNICAL DATASHEET

Page: 1 / 2

Description : W/B PUTTY
Product Number : 211-209-1000

Description : Pigmented and highly filled waterborne filler to be applied on filler

machines in the direct coating / printing process of wood fiberboards. Due to high filling properties, the product produces excellent surface

after sanding for subsequent coating.

**Characteristics** 

Viscosity: 300 - 350 dPa.s in Dynamic measurement (#2) at 25°C.

Density :  $1.69 \pm 0.02 \text{ kg/l}$ 

Solid Content : 70 - 75%

VOC : Max 3%

Pigments : Does not contain any lead, cadmium or chromate.

Classification : Complies with the Environmental Protection Act of 1990.

**Application** 

Preparation : Stir well and check before use.

Hardener : Not applicable

Thinner : Use water to adjust viscosity if required.

Viscosity : As delivered

Film Weight : Apply 40 - 60 g/m<sup>2</sup>.

Mode : Apply in roller machine.

Drying : 12-15 sec at 120°C jet air with airspeed of 23 m/s.

50 sec at 150°C circulatory air with airspeed of 5-7 m/s and a

circulatory to fresh air proportion 8:2.

Substrate : This product is specially formulated to be applied as filler coat on

fiberboards. The substrate should be calibrated to a maximum thickness variation of 0.2 mm. In all cases, substrates must be free

of dust.

TEKNOS (M) Sdn. Bhd. PLO 577, Jalan Keluli 8 Kawasan Perindustrian Pasir Gudang 81700 Pasir Gudang, Johor, Malaysia T +60 7 251 5115 F +60 7 251 4115 info.malaysia@teknos.com www.teknos.my



## TECHNICAL DATASHEET

Page: 2 / 2

Description : W/B PUTTY

Product Number : 211-209-1000

Please consult our technical staff prior to other applications.

**Storage** 

Shelf Life : 12 months

Conditions : The product should be stored between 5°C and 35°C. Keep

container tightly closed and in a well ventilated place. Keep away from sources of ignition, heat and oxidizing substances. Higher temperatures reduce the shelf life. Protect from sunlight and frost.

**Delivery** 

Packaging : Available in 20 kg pails.

Delivery Time : Please allow 6 working days of production and transportation.

**Cleaning** : Clean equipment with water immediately after use.

**Precautions** : Refer to Safety Data Sheet.

**Health & Safety** : Refer to Safety Data Sheet.