

TECHNICAL DATASHEET

Description : **W/B BASECOAT**

Product Number : **231-201-1003**

Description : Extra white pigmented waterborne basecoat to be applied in roller machines in the direct coating / printing process of fiber boards and particle boards. Due to good levelling and hiding properties, this product gives an excellent base for subsequent coating layers with Teknos waterborne printing ink and UV-curable topcoat.

Characteristics

Viscosity : 35 - 40 sec. in DIN 6mm at 30°C.

Density : 1.5 ± 0.2 kg/l

Solid Content : 58 - 62%

VOC : Max 2%

Application

Preparation : Stir well and check before use.

Hardener : Not applicable

Thinner : Use water to adjust viscosity if required.

Viscosity : As delivered

Film Weight : Apply 30 - 40 g/m².

Mode : Apply in roller machine.

Drying :
15 sec at 140°C jet air with airspeed of 25-30 m/s.
30 sec at 130°C circulatory air with airspeed of 5-7 m/s and a circulatory to fresh air proportion 8:2.

For other drying methods please note that the temperature of substrate's surface must exceed 50°C when leaving the drying device.

Substrate : This product is specially formulated to be applied as basecoat on TEKNOS waterborne fillers.

TECHNICAL DATASHEET

Page: 2 / 2

Description : W/B BASECOAT
Product Number : 231-201-1003

Please consult our technical staff prior to other applications.

Storage

Shelf Life : 12 months

Conditions : The product should be stored between 5°C and 35°C. Keep container tightly closed and in a well ventilated place. Keep away from sources of ignition, heat and oxidizing substances. Higher temperatures reduce the shelf life. Protect from sunlight and frost.

Delivery

Packaging : Available in 20 kg pail, 200 kg drum and 1250 kg IBC.

Delivery Time : Please allow 6 working days of production and transportation.

Cleaning : Clean equipment with water immediately after use.

Precautions : Refer to Safety Data Sheet.

Health & Safety : Refer to Safety Data Sheet.