TEKNOS TREFFERT (M) Sdn. Bhd. T + 60.7 251 5115 (formerly known as Treffert Coatings (S.E.A.) F + 60.7 251 4115

Sdn. Bhd.)

PLO 577, Jalan Keluli 8 Kawasan Perindustrian Pasir Gudang 81700 Pasir Gudang, Johor, Malaysia T +60 7 251 5115 F +60 7 251 4115 info.malaysia@teknos.com

www.teknos.my



TECHNICAL DATASHEET

Page: 1 / 2

Description : W/B PUTTY
Product Number : 211-209-1000

 Pigmented and highly filled waterborne filler to be applied on filler machines in the direct coating / printing process of wood fiberboards.
 Due to high filling properties, the product produces excellent surface

after sanding for subsequent coating.

Characteristics

Description

Viscosity: 300 - 350 dPa.s in Dynamic measurement (#2) at 25°C.

Density : $1.69 \pm 0.02 \text{ kg/l}$

Solid Content : 70 - 75%

VOC : Max 3%

Pigments : Does not contain any lead, cadmium or chromate.

Classification : Complies with the Environmental Protection Act of 1990.

Application

Preparation : Stir well and check before use.

Hardener : Not applicable

Thinner : Use water to adjust viscosity if required.

Viscosity : As delivered

Film Weight : Apply 40 - 60 g/m².

Mode : Apply in roller machine with a shore hardness of offset rollers of 40-

50 (Isobutylene / Isoprene-Copolymer or EPDM-Prepolymer).

Drying : 12-15 sec at 120°C jet air with airspeed of 23 m/s.

50 sec at 150°C circulatory air with airspeed of 5-7 m/s and a

circulatory to fresh air proportion 8:2.

Substrate : This product is specially formulated to be applied as filler coat on

fiberboards. The substrate should be calibrated to a maximum thickness variation of 0.2 mm. In all cases, substrates must be free

TEKNOS TREFFERT (M) Sdn. Bhd. T +60 7 251 5115 (formerly known as Treffert Coatings (S.E.A.) F +60 7 251 4115 Sdn. Bhd.) F +60 7 251 4115 info.malaysia@tek

PLO 577, Jalan Keluli 8

Kawasan Perindustrian Pasir Gudang 81700 Pasir Gudang, Johor, Malaysia T +60 7 251 5115 F +60 7 251 4115 info.malaysia@teknos.com www.teknos.my



TECHNICAL DATASHEET

Page: 2 / 2

Description : W/B PUTTY

Product Number : 211-209-1000

of dust.

Please consult our technical staff prior to other applications.

Storage

Shelf Life : 12 months

Conditions : Protect from sunlight and frost. Keep container tightly closed and in

a well ventilated place. Keep away from sources of ignition, heat and

oxidizing substances.

To be stored at 5 - 35 °C.

Delivery

Packaging : Available in 20 kg pails.

Delivery Time : Please allow 6 working days of production and transportation.

Quantity : Except for trial, minimum quantity is 100kg per individual product.

Cleaning : Clean equipment with water immediately after use.

Precautions: Refer to Safety Data Sheet.

Health & Safety : Refer to Safety Data Sheet.