

TECHNICAL DATASHEET

Page: 1 / 2

Description : **W/B ADHESIVE COAT**

Product Number : **221-204-1001**

Description : White pigmented waterborne adhesion promoter to be applied on roller machines in the direct coating/printing process of fiber boards. Due to its excellent wetting property, the products provide excellent adherence to TEKNOS TREFFERT UV Topcoat.

Characteristics

Viscosity : 50 - 60 sec. in DIN 6mm at 30°C.
Density : 1.6 ± 0.1 kg/l
Solid Content : 58 - 62%
VOC : Max 3%
Pigments : Does not contain any lead, cadmium or chromate.
Classification : Complies with the Environmental Protection Act of 1990.

Application

Preparation : Stir well and check before use.
Hardener : Not applicable
Thinner : Use water to adjust viscosity if required.
Viscosity : As delivered
Film Weight : Apply 20 - 30 g/m².
Mode : Apply in roller machine with a shore hardness of offset rollers of 40-50 (Isobutylene / Isoprene-Copolymer or EPDM-Prepolymer).
Drying : 12-15 sec at 120°C jet air with airspeed of 23 m/s.
50 sec at 150°C circulatory air with airspeed of 5-7 m/s and a circulatory to fresh air proportion 8:2.

Substrate : This product is especially formulated to be applied as adhesion promoter on TEKNOS TREFFERT UV Topcoat in direct printing for wood composite like MDF, HDF, chipboards and plywood.

TECHNICAL DATASHEET

Page: 2 / 2

Description : W/B ADHESIVE COAT
Product Number : 221-204-1001

Please consult our technical staff prior to other applications.

Storage

Shelf Life : 12 months
Conditions : Protect from sunlight and frost. Keep container tightly closed and in a well ventilated place. Keep away from sources of ignition, heat and oxidizing substances.

To be stored at 5 - 35 °C.

Delivery

Packaging : Available in 20 kg pails.
Delivery Time : Please allow 6 working days of production and transportation.
Quantity : Except for trial, minimum quantity is 100kg per individual product.

Cleaning : Clean equipment with water immediately after use.

Precautions : Refer to Safety Data Sheet.

Health & Safety : Refer to Safety Data Sheet.