



ALPOCRYL LE 5393

SOLVENT-BASED 2C-POLYURETHANE TOP COAT

THE ALLROUNDER

ALPOCRYL LE 5393 is a high-quality, solvent-based 2C-polyurethane top coat. This product has outstanding versatility being suitable for a wide variety of substrates including wood, MDF, chipboard, glass, metal and plastic. It has excellent adhesion properties on all surfaces and very high covering power. ALPOCRYL LE 5393 is suitable as a coating in coating system for mixing equipment. This permits the mixture of almost any colour.

THE PROVEN SOLUTION

The top coat has already proven its worth in numerous practical applications. Manufacturers from various European countries use the coating for PVC windows, interior doors, kitchen surfaces, furniture, interior fittings (including yachts), coated glass elements and even for solariums and MRT equipment.

CALL US

Get expert advice on the use of ALPOCRYL LE 5393 or other Teknos coating products. Our technical customer service is always at your disposal when it comes to developing the optimum coating solutions and systems.

MAIN FEATURES

Very high resistance to weather conditions, chemical and mechanical stress

Excellent adhesion

Easy application

UV-resistant and absolutely light-fast

Very fast drying

The look and feel can also be adjusted and reinforced by adding structural powder



Our mission is to extend the life of your products by providing intelligent, technically advanced paint and coating solutions for even better protection - always in close collaboration with our customers.

 **TEKNOS**

PRODUCT FACTS

ALPOCRYL LE 5393

SOLVENT-BASED 2C-POLYURETHANE TOP COAT

COLOURS	In compliance with RAL and NCS S shade cards
GLOSS LEVEL	Satin gloss 40
APPLICATION	<ul style="list-style-type: none"> ▪ Gravity feed gun ▪ Airless (airmix) spraying
CONTAINER SIZE	<ul style="list-style-type: none"> ▪ Coating: 1 l, 5 l, 10 l ▪ Hardener: 0.5 l, 1 l, 2.5 l, 5 l
MIXING RATIO	10:1

DRYING TIMES	
Dust dry after	10 minutes
Touch dry after	30 minutes
Sandable after	60 minutes
Workable after	2 to 48 hours max.

COATING RECOMMENDATION

GALVANISED SUBSTRATES AND PLASTICS ONLY UPON REQUEST

	MDF/HDF/GF	WOOD	METAL	PVC	GLASS*
PRIMER	RAPIFILL 1080 or ISOFILL 1070	ALPOCRYL LE 5393	ALPOTECT PHOSPHAT-GRUND 510	REINIGUNGSMITTEL 1530-98	VTM 4118*
INTERMEDIATE SANDING	Grain 220-240	Grain 220-240			
RECOATING	ALPOCRYL LE 5393	ALPOCRYL LE 5393	ALPOCRYL LE 5393	ALPOCRYL LE 5393	ALPOCRYL LE 5393

* Please refer to our VTM 4118

For further technical information refer to data sheet no. 5393



WE MAKE THE WORLD LAST LONGER

TEKNOS GB
7 LONGLANDS RD
BICESTER
OXON OX26 5AH
T 01869 208005

TEKNOS IRELAND
54 BALLYMOUGHAN RD
MAGHERAFELT
BT45 6HN
T 02879 301472

sales@teknos.co.uk
www.teknos.co.uk

