



# SUPREMO KLARLACK 3990

Solvent-based 2C PUR Primer and Top Coat

## THE PERFECT COMPANION FOR YOUR INTERIORS

The 2C PUR clear coating is mainly used for interior applications, furniture manufacturing as well as in general carpentry work to achieve a high-quality surface. Especially suitable for use on vertical surfaces due to its special thixotropic properties.

## IDEAL FOR A WIDE RANGE OF APPLICATIONS

SUPREMO KLARLACK 3990 creates a surface that looks luxurious and feels pleasant. Its easy application on open and closed-pore woods makes it particularly suitable as a top coat for various surfaces. Due to its peroxide resistance it can also be used on bleached woods. In addition, coloured surfaces can also be finished with SUPREMO KLARLACK 3990 due to its versatile performance.

## CONTACT US

Calling Teknos is a quick and easy way to get expert advice on the use of SUPREMO KLARLACK 3990 or other Teknos coating products. Our technical customer service is always at your disposal when it comes to developing optimum coating solutions and systems.



## MAIN FEATURES

- Very fast drying
- Excellent adhesion
- Easy application
- Good grain-accentuating effect (also available for lightening – SUPREMO AUFHELLEND 2025)
- Can be used on wood that has been bleached with peroxide
- Very hard-wearing

*Our mission is to extend the life of your products by providing intelligent, technically advanced paint and coating solutions for even better protection – always in close collaboration with our customers.*





**CLEAR FAST-DRYING, GRAIN  
ACCENTUATING,  
SOLVENT-BORNE  
2C PRIMER AND  
TOPCOAT FOR INTERIOR  
JOINERY.**



## PRODUCT DATA

- GLOSS LEVEL**
- Natural matt 02, Dull matt 05, Matt 15, Satin matt 40, Satin gloss 50, Gloss 90
- APPLICATION**
- Gravity feed gun
  - Airless (airmix) spraying
- CONTAINER SIZE**
- Paint: 5 l, 10 l, 25 l
  - Hardener: 1 l, 2.5 l, 5 l
- MIXING RATIO**
- 10:1

## DRYING TIMES

- DUST DRY AFTER** 15 minutes
- TOUCH DRY AFTER** 30 minutes
- SANDABLE AFTER** 3 hours
- RECOATABLE AFTER** 3 hours
- FULLY DRY AFTER** 10 days

## COATING RECOMMENDATION

	UNTREATED WOOD SUBSTRATE	MDF BOARDS
<b>PRE-SANDING</b>	Grain 150-180	Grain 180-220
<b>STAIN</b>	STAIN IF REQUIRED	
<b>PRIMER</b>	SUPREMO KLARLACK 3990	SUPREMO KLARLACK 3990
<b>INTERMEDIATE SANDING</b>	Grain 240-320	Grain 240-320
<b>RECOATING</b>	SUPREMO KLARLACK 3990	SUPREMO KLARLACK 3990

For further technical information refer to data sheet no. 3990

TEKNOS GBI  
7 LONGLANDS RD  
BICESTER  
OXON OX26 5AH  
T 01869 208005

TEKNOS IRELAND  
54 BALLYMOUGHAN RD  
MAGHERAFELT  
BT45 6HN  
T 02879 301472

sales@teknos.co.uk  
www.teknos.co.uk

 **TEKNOS**