

# INFRALIT EP/PE 8235

## Epoxy/Polyester Powder

---

<b>PAINT TYPE</b>	INFRALIT EP/PE 8235 powder coating based on epoxy and polyester resin, which at elevated temperatures melts, cures and forms the final paint film.
<b>USAGE</b>	INFRALIT EP/PE 8235 Epoxy/Polyester Powder is suitable for coating objects where anti-microbial properties are needed. INFRALIT EP/PE 8235 Epoxy/Polyester Powder's anti-microbial properties are based on the active ingredients of noble metals.
<b>SPECIAL PROPERTIES</b>	The mechanical and chemical resistance and the anti-corrosive properties of INFRALIT EP/PE 8235 are almost equal to those of epoxies. On outdoor exposure like epoxy/polyester powders in general, has tendency towards matting down (chalking) similar to that of pure epoxies. On the other hand, it's tendency to yellow on overbaking and exposure to ultraviolet light is minor as compared with epoxy powders.
<b>APPROVALS</b>	INFRALIT EP/PE 8235 Epoxy/Polyester Powder fulfils the requirements of ISO 22196 for preventing the growth of certain microbes.

---

**TECHNICAL DATA**

<b>Spraying</b>	Suitable for both tribo charging and corona charging sprays.
<b>Colours</b>	By agreement.
<b>Gloss grades</b>	EP/PE 8235-30: matt EP/PE 8235-74: semigloss, the coating provides ESD protection EP/PE 8235-75: semigloss EP/PE 8235-90: gloss
<b>Solids</b>	100%
<b>Specific gravity</b>	Abt. 1,25 - 1,70 kg/dm <sup>3</sup> depending on colour
<b>Spreading rate</b>	4 - 15 m <sup>2</sup> /kg depending on the film thickness
<b>Film thickness</b>	One application gives a film thickness of 40 - 150 µm.
<b>Curing time</b>	EP/PE 8235-74, -75 and -90: 15 min/180°C (metal temperature) EP/PE 8235-30: 10 min/200°C (metal temperature)
<b>Packages</b>	20 kg
<b>Storage</b>	In dry and cool conditions.

---

**SAFETY PRECAUTIONS**

The powder itself is non-flammable, but with air it can form an explosive mixture that in presence of adequate ignition energy ignites. The lower explosive limit is about 70 g/m<sup>3</sup> (Bundesanstalt für Materialprüfung). Ventilation of the spray booth should be adjusted so that the concentration of powder in the air is less than 50% of the lower explosive limit value. On calculation of the powder concentration in the spray booth, the powder deposited on the workpiece is not taken into account. In order to avoid the discharge of powder from the booth into adjacent working spaces, the speed of air flow in the apertures of the booth must not fall below 0.5 m/s. Spray painters should wear dust masks and protective gloves. Any spatter of powder on the skin should be washed off with water and soap.

**DIRECTION FOR USE****Surface preparation**

COLD-ROLLED SURFACES: Grease removal and iron-phosphating. Zinc phosphating is also required if the workpiece is destined for outdoor exposure or will be subjected to exceptional strain indoors.

ALUMINIUM SURFACES: Degrease by e.g. alkali wash. Surfaces to be exposed to severe atmospheric conditions should also be chromated.

HOT-DIP-GALVANIZED AND ZINC-ELECTROPLATED SURFACES: Remove grease and white rust by e.g. alkali wash. Depending on exposure conditions, zinc phosphating or chromating is also required.

HOT-ROLLED SURFACES: Blast-clean to preparation grade Sa 2½ (ISO 8501-1).

The profile of the blast-cleaned surface must be at least medium (G). See standard ISO 8503-2.

**FILM PROPERTIES**

Substrate cold-rolled steel, curing time 15 min/180°C:

**Physical properties**

Flexibility (Erichsen, ISO 1520)	7 mm
Impact resistance (Erichsen, SFS EN ISO 6272)	
- direct	40 kgcm
- reverse	40 kgcm
Pendulum hardness (König, SFS 3642)	180 s
Flexibility (SFS ISO 6860)	less than 5 mm
Adhesion (cross-cut test, EN ISO 2409)	GT 0

The information of this data sheet is normative and based on laboratory tests and practical experience. Teknos guarantees that the product quality conforms to our quality system. Teknos accepts, however, no liability for the actual application work, as this is to a great extent dependent on the conditions during handling and application. Teknos accepts no liability for any damage resulting from misapplication of the product. This product is intended for professional use only. This implies that the user possesses sufficient knowledge for using the product correctly with regard to technical and working safety aspects. The latest versions of Teknos data sheets, material safety data sheets and system sheets are on our home pages [www.teknos.com](http://www.teknos.com).



EN\_1471\_Tuoteseloste.pdf