

„MEŽA UN KOKSNES PRODUKTU PĒTNIECĪBAS UN ATTĪSTĪBAS INSTITŪTS” SIA  
VAT No. LV 43603022749  
Dobeles iela 41, Jelgava, LV-3001, Latvia  
Phone +371 63010605 \* E-mail meka@e-koks.lv \* Web www.e-koks.lv



## Classification of reaction to fire in accordance with EN 13501-1:2018

Issue number: K97/2022

Date of issue: 19.09.2022.

**Sponsor:** Teknos AS.

Address: Industrivej 19, 6580 Vamdrup, Denmark.

Reg. No. 85551612.

**Manufacturer and owner of classification report:** Teknos AS.

**Prepared by:** SIA “Meža un koksnes produktu pētniecības un attīstības institūts” (*Forest and Wood Products Research and Development Institute Ltd*).

Test performed at: SIA “Meža un koksnes produktu pētniecības un attīstības institūts” (Forest and Wood Products Research and Development Institute Ltd), “Pienavas katlu māja”, Pienava, Džūkstes pagasts, Tukuma novads, LV-3147, Latvia (“Pienava heat plant”, Pienava, Džūkste parish, Tukums region, LV-3147, Latvia).

**Product name:** TEKNOSAFE FLAME GUARD 2477-00 and TEKNOSAFE FLAME PROTECT 2478-00.

Laboratory involved in testing is accredited by the Latvian National Accreditation Bureau (LATAK) according to the standard LVS EN ISO/IEC 17025 under the terms of Latvian legislation with reg. No. T-316. Laboratory is a notified body with reg. No. NB 2040 under construction product regulation No. 305/2011.

*Classification report refers only to these test objects. This classification report may not be reproduced otherwise than in full text, excepted with the prior written approval of the Forest and Wood Products Research and Development Institute*

## 1. Introduction

This classification report defines the reaction to fire classification assigned to TEKNOSAFE FLAME GUARD 2477-00 and TEKNOSAFE FLAME PROTECT 2478-00 in accordance with the procedures given in EN 13501-1:2018.

## 2. Details of classified product

### 2.1. General

TEKNOSAFE FLAME GUARD 2477-00 and TEKNOSAFE FLAME PROTECT 2478-00 is defined as fire retardant treatment for wood-based products.

### 2.2. Product description

- Product name: TEKNOSAFE FLAME GUARD 2477-00 and TEKNOSAFE FLAME PROTECT 2478-00.
- Manufacturer: Teknos AS.
- Materials used for manufacturing:
  - Compound substrate made of 9 mm standard spruce plywood with 450 kg/m<sup>3</sup> density and 12 mm wood particleboard substrate with density 680 kg/m<sup>3</sup>;
  - Base coat: TEKNOSAFE FLAME GUARD 2477-00 with 250 g/m<sup>2</sup> consumption;
  - With or without topcoat: TEKNOSAFE FLAME PROTECT 2478-00 with 100 g/m<sup>2</sup> consumption.
- Colour: clear.

## 3. Test reports and test results in support of classification

### 3.1. Specific conditions

Not applicable

### 3.2. Test reports

Name of laboratory	Name of sponsor	Test reports	Test method
SIA „ Meža un koksnes produktu pētniecības un attīstības institūts” Testing Laboratory	Teknos AS	6682-1/2022	EN 13823:2020
SIA „ Meža un koksnes produktu pētniecības un attīstības institūts” Testing Laboratory	Teknos AS	6682-2/2022	EN ISO 11925-2:2020

### 3.3. Test results

Test method	Parameter	Number of tests	Results	
			Continuous parameter mean	Compliance parameters
EN 13823:2020	<i>FIGRA</i> <sub>0,2MJ</sub> (W/s)	5	86.0	(-)
	<i>FIGRA</i> <sub>0,4MJ</sub> (W/s)		85.8	(-)
	<i>THR</i> <sub>600s</sub> (MJ)		7.2	(-)
	<i>LFS</i>		no	Compliant
	<i>SMOGRA</i> (m <sup>2</sup> /s <sup>2</sup> )		7.8	(-)
	<i>TSP</i> <sub>600s</sub> (m <sup>2</sup> )		45.9	(-)
	Flaming droplets <10s Flaming droplets >10s		(-) (-)	Compliant Compliant
EN ISO 11925-2:2020  Exposure time 30 s. Test duration 60 s.	Flame spread (Fs)	12	(-)	Compliant
	Ignition of filter paper		(-)	Compliant
	Flaming droplets/particles		(-)	Compliant
(-) not applicable				

## 4. Classification and field of application

### 4.1. Reference of classification

This classification has been carried out in accordance with clause 11 of EN 13501-1:2018.

### 4.2. Classification

TEKNOSAFE FLAME GUARD 2477-00 and TEKNOSAFE FLAME PROTECT 2478-00 in relation to its reaction to fire behaviour is classified:

B

The additional classification in relation to smoke production is:

s1

The additional classification in relation to flaming droplets/particles is:

d0

The format of the reaction to fire classification for construction product excluding floorings and linings is:

Fire behaviour		Smoke production			Flaming droplets	
B	-	s	1	,	d	0

**Reaction to fire classification: B-s1, d0**

### 4.3. Field of application

4.3.1 This classification is valid for the following product end use applications:

Product is intended to use as fire retardant treatment for wood-based products.

4.3.2. This classification is also valid for following product parameters:

Coatings:

- valid for coating system as tested, with or without tested topcoat.

Substrates:

- applied to wood substrate in accordance with EN 13238 of at least Euroclass D-s2, d0 with a thickness of at least 18 mm and a substrate density  $\geq 433 \text{ kg/m}^3$ ;

or

- applied to a first wood substrate in accordance with EN 13238 of at least Euroclass D-s2,d0 with a thickness of at least 8 mm and having a density of  $\geq 338 \text{ kg/m}^3$ . The first substrate shall be mounted direct to a second wood-based substrate in accordance with EN 13238 of at least Euroclass D-s2, d0 with a thickness of at least 10 mm and having a density of  $\geq 510 \text{ kg/m}^3$ ;

or

- applied to a first wood-based substrate in accordance with EN 13238 of at least Euroclass D-s2, d0 with a thickness of at least 8 mm and having a density of  $\geq 338 \text{ kg/m}^3$ . The first substrate shall be mounted directly to a second substrate of gypsum plaster board or any end use substrate of Euro classes A1 or A2-s1, d0 at least 10 mm thick having a density  $\geq 510 \text{ kg/m}^3$ .

Mounting:

- mounted with or without ventilated or unventilated air gap. The substrate behind the product shall consist of mineral wool with Euroclass A1 and a thickness of at least 20 mm and a density  $\geq 38 \text{ kg/m}^3$  or a gypsum plasterboard (paper faced) or any end use substrate of Euroclass A1 or A2-s1, d0 at least 10 mm thick having a density  $\geq 510 \text{ kg/m}^3$ ;
- valid for untreated wood battens or other Euroclass A1 or A2-s1, d0 products;
- valid for mechanically fixing;
- valid for product application with standard vertical and horizontal joints;
- valid for vertical and horizontal arrangements.

Color:

- valid for clear colour tone.

### 5. Limitations.

5.1. No restrictions on the duration of validity of this classification report as long as the product specifications remain unchanged.

5.2. This document does not represent type approval or certification of the product.

Prepared by



E. Bukšāns

(signature and name)

Reviewed by



K. Būmanis

(signature and name)

THIS DOCUMENT IS SIGNED BY SECURE ELECTRONIC SIGNATURE AND CONTAINS A TIME STAMP  
(Signature validity can be checked: <https://www.eparaksts.lv/en>)